

Technical Data Sheet

❖ Alfater XL®

MOCOM

ALFATER XL A80I 4FC0010

Base Polymer	Thermoplastic Vulcanisate (PP+EPDM)
Colour	natural color,bright inherent color
Service Temperature	max. range (depending on load, geometry, etc.) -40-125 °C
Special Features	food contact,compliant EN 71-3,good colorability,good weathering resistance,good chemical resistance,good ozone reistance,good hot air resistance,good hydrolysis resistant,easy flow
Market Segment	packaging,household goods,food processing industry,toys
Application Area	injection moulded parts
Typical Applications	seals,sealing lip,handles,soft touch elements,protection caps,caps / closures,containers,kitchen ware,2K components
Adhesion to	Polypropylene Homopolymer,Polypropylene Copolymer,Polyethylene,Thermoplastic Vulcanisate (PP+EPDM),Thermoplastic Olefin Elastomer,Thermoplastic Elastomer general

Pre-Drying Conditions	in a dry air (dessiccant) dryer 70-80 °C for 2-4 h max. moisture content <0,10 %
Processing Injection Moulding	melt temperature 190-220 °C mould temperature 10-60 °C injection speed middle - high back pressure (hydraulic) >3 bar holding pressure 50-70% of injection pressure
Storage	dry, protected from light not above 30°C tightly sealed
Minimum Shelf Life	months <12

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Stress at 100% Elongation (Type 2)	3.8	MPa	ISO 37
Tensile Strength (Type 2)	5.9	MPa	ISO 37
Tear Strength (Method Ba)	38	kN/m	ISO 34-1
Elongation at Break (Type 2)	400	%	ISO 37
Shore Hardness A (15s)	80	-	ISO 868
Thermal Properties			
Compression Set (22h / 100°C / 25% / Type A)	61	%	ISO 815
Compression Set (22h / 70°C / 25% / Type A)	54	%	ISO 815
Compression Set (72h / 22°C / 25% / Type A)	36	%	ISO 815
Compression Set (72h / 125°C / 25% / Type A)	80	%	ISO 815

Technical Data Sheet

❖ Alfater XL®

MOCOM

ALFATER XL A80I 4FC0010

Electrical Properties

Tracking Resistance (CTI)	600	-	IEC 60112
---------------------------	-----	---	-----------

Rheological Properties

Shrinkage (lengthwise, 24h)	1.3 - 1.7	%	ISO 294-4
Shrinkage (lateral, 24h)	1 - 1.4	%	ISO 294-4
Spiral Flow (2 mm wall thickness)	73	cm	-

Physical Properties

Density	930	kg/m³	ISO 1183
---------	-----	-------	----------

Ageing Properties

Ozone resistance (method A)	passed	-	ISO 1431-1A
-----------------------------	--------	---	-------------