

Technical Data Sheet

Alfater XL® ECO

MOCOM

ALFATER XL ECO D50I 2GP0000

Base Polymer	Thermoplastic Vulcanisate (PP+EPDM)
Colour	black
Service Temperature	max. range (depending on load, geometry, etc.) -40-125 °C
Special Features	Polymer recyclate, good weathering resistance, good chemical resistance, good ozone resistance, good hot air resistance, good hydrolysis resistant
Market Segment	Automotive, building and construction, do-it-yourself, electrical and electronic, Machinery, Furniture
Application Area	injection moulded parts, blow moulded parts
Typical Applications	seals, sealing lip, handles, racking / shelving, impact protection / shock absorber, protection caps, cable ducts, bellows, 2K components
Adhesion to	Polypropylene Homopolymer, Polypropylene Copolymer, Polyethylene, Thermoplastic Vulcanisate (PP+EPDM), Thermoplastic Olefin Elastomer, Thermoplastic Elastomer general

Pre-Drying Conditions	in a dry air (dessiccant) dryer 70-80 °C for 2-4 h max. moisture content <0,10 %
Processing Injection Moulding	melt temperature 195-240 °C mould temperature 10-70 °C injection speed high back pressure (hydraulic) >4 bar holding pressure 50-70% of injection pressure press blow molding melt temperature 190-210 °C
Storage	dry, protected from light tightly sealed

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Stress at 100% Elongation (Type 2)	12.7	MPa	ISO 37
Tensile Strength (Type 2)	14.9	MPa	ISO 37
Tear Strength (Method Ba)	93	kN/m	ISO 34-1
Elongation at Break (Type 2)	500	%	ISO 37
Shore Hardness D (15s)	50	-	ISO 868
Thermal Properties			
Compression Set (22h / 100 °C / 25% / Type A)	87	%	ISO 815
Compression Set (22h / 70 °C / 25% / Type A)	80	%	ISO 815
Compression Set (72h / 22 °C / 25% / Type A)	70	%	ISO 815
Compression Set (72h / 125 °C / 25% / Type A)	98	%	ISO 815

Technical Data Sheet

Alfater XL[®] ECO



ALFATER XL ECO D50I 2GP0000

Electrical Properties

Tracking Resistance (CTI)	600	-	IEC 60112
---------------------------	-----	---	-----------

Rheological Properties

Shrinkage (lengthwise, 24h)	1.8 - 2.2	%	ISO 294-4
Shrinkage (lateral, 24h)	1.3 - 1.7	%	ISO 294-4
Spiral Flow (2 mm wall thickness)	35	cm	-

Physical Properties

Density	990	kg/m ³	ISO 1183
---------	-----	-------------------	----------

Ageing Properties

Ozone resistance (method A)	passed	-	ISO 1431-1A
-----------------------------	--------	---	-------------

Ecological Properties

Global Warming Potential (GWP)	0.99	kg CO ₂ eq./kg	ISO 14040, 14044
--------------------------------	------	---------------------------	------------------

Flammability

Flammability (1.5 mm)	HB	class	UL 94
Flammability (3.0 mm)	HB	class	UL 94
Glow Wire (GWFI, 650 °C, 2.0mm)	passed	-	DIN EN 60695
Fire behavior FMVSS (2.0 mm)	passed	-	FMVSS 302/DIN 75200

Diagrams

Viscosity-shear rate

