

ALCOM PC 740/4 GF20 UV WT1105-13LD

(Last update: 21.12.2022)

MOCOM

Base Polymer	Polycarbonate
Filler/Additive System	20 % glass fibres, special filler, UV stabilised
Special Features	translucent, light scattering, high light diffusion
Market Segment	Automotive, Lighting
Application Area	lighting, light transparent components
Typical Applications	lamp covers, display elements, operating elements

Pre-Drying Conditions	120 °C in a dry air (dessiccant) dryer for 2-3 h max. moisture content <0,02 %
Processing Injection Moulding	melt temperature 290-320 °C mould temperature 80-130 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	5800	MPa	ISO 178
Flexural Strength	150	MPa	ISO 178
Tensile Modulus	6000	MPa	ISO 527
Tensile Strength at Break	95	MPa	ISO 527
Tensile Elongation at Break	2.7	%	ISO 527
Impact Strength (Charpy, 23°C)	50	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	45	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	7.5	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	6	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	145	°C	ISO 306
HDT / A (1,8 MPa)	140	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	11	cm ³ /10min	ISO 1133
MVR temperature	300	°C	-
MVR load	1.2	kg	-
Shrinkage (lengthwise, 24h)	0.4 - 0.7	%	ISO 294-4
Shrinkage (lateral, 24h)	0.4 - 0.8	%	ISO 294-4
Physical Properties			
Density	1340	kg/m ³	ISO 1183



ALCOM PC 740/4 GF20 UV WT1105-13LD

(Last update: 21.12.2022)



Flammability

Flammability (0.75 mm)	V-2	class	UL 94
Flammability (1.5 mm)	HB	class	UL 94
Glow Wire (GWFI, 850 °C, 1.0mm)	passed	-	DIN EN 60695
Glow Wire (GWFI, 850 °C, 2.0mm)	passed	-	DIN EN 60695

Optical Properties

Total Transmission T(Y) (d=1,0mm, A, 2°)	53	%	ISO 13468
Total Transmission T(Y) (d=2,0mm, A, 2°)	37	%	ISO 13468
Total Transmission T(Y) (d=3,0mm, A, 2°)	27	%	ISO 13468
Total Transmission T(Y) (d=4,0mm, A, 2°)	21	%	ISO 13468
Haze T(Y) (d=1,0 mm, A, 2°)	95.5	%	ISO 13468
Haze T(Y) (d=2,0 mm, A, 2°)	95.5	%	ISO 13468
Haze T(Y) (d=3,0 mm, A, 2°)	95.5	%	ISO 13468
Haze T(Y) (d=4,0 mm, A, 2°)	95.5	%	ISO 13468
Half Power Angle T(Y) (d=1,0mm, A, 2°)	47	°	-
Half Power Angle T(Y) (d=2,0mm, A, 2°)	60	°	-
Half Power Angle T(Y) (d=3,0mm, A, 2°)	62	°	-
Half Power Angle T(Y) (d=4,0mm, A, 2°)	63	°	-


ALCOM PC 740/4 GF20 UV WT1105-13LD

(Last update: 21.12.2022)


MOCOM

Diagrams


Stress-Strain



Angle dependent relative irradiance



Spectrum



Liability Exclusion

These are guide values and not a specification. The test values mentioned are representative values only and not binding minimum or maximum figures. These test values have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions.

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT**



ALCOM PC 740/4 GF20 UV WT1105-13LD

(Last update: 21.12.2022)



LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.