

**ALTECH PA66 ECO 1000/116**

(Last update: 20.03.2023)

**MOCOM**

Base Polymer	Polyamide 66
Special Features	impact modified, high heat stabilised, contains recycled material
Market Segment	Automotive, building and construction, various
Application Area	fixtures / fittings, various
Typical Applications	housing and automotive trim unpainted, cable ties, clips, various
Approvals	GMW15702

Pre-Drying Conditions      80 °C in a dry air (dessiccant) dryer  
for 2-12 h  
dependant on moisture content  
0,15 % max. moisture content

Processing Injection Moulding      melt temperature 270-290 °C  
mould temperature 40-80 °C

Storage      dry, protected from light

Properties	Value	Dimension	Test Norm
<b>Mechanical Properties</b>			
Flexural Modulus	2400	MPa	ISO 178
Flexural Stress (3.5% Strain)	80	MPa	ISO 178
Tensile Modulus	2600	MPa	ISO 527
Tensile Strength	60	MPa	ISO 527
Tensile Elongation at Break	25	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m <sup>2</sup>	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	8	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal Properties</b>			
HDT / A (1,8 MPa)	60	°C	ISO 75-1/-2
<b>Rheological Properties</b>			
Shrinkage (lengthwise, 24h)	1.4 - 1.8	%	ISO 294-4
Shrinkage (lateral, 24h)	1.6 - 2	%	ISO 294-4
<b>Physical Properties</b>			
Density	1120	kg/m <sup>3</sup>	ISO 1183
<b>Ecological Properties</b>			
Global Warming Potential (GWP)	0.42	kg CO <sub>2</sub> eq./kg	ISO 14040, 14044

**Additional Information**

When using raw materials from a recycling process, as with prime materials, ferrous / non-ferrous residues can never be completely excluded. To minimize the risk of possible effects of such residues, MOCOM uses extensive detection and separation systems in the production process of its compounds. However, even these quality assurance systems cannot guarantee that the resulting product is 100% free of such residues. Therefore, we recommend our customers to additionally use their own detection and separation systems adapted to



## ALTECH PA66 ECO 1000/116

(Last update: 20.03.2023)



their respective process. For further questions and specific advice in connection with MOCOM products, please do not hesitate to contact our application engineering department. The ecological properties listed in this document were calculated for a production in one of our European plants. Data for production in the United States or China can be provided by sending a request to the following address.  
technical@mocom.eu

### Liability Exclusion

These are guide values and not a specification. The test values mentioned are representative values only and not binding minimum or maximum figures. These test values have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions.

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

**Healthcare uses:** the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

**Important:** irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.