

Adsyl 7572 XCP
PP OTHERS

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	5.5	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	128	°C	ISO 11357-1/-3
Temp. of deflection under load (0.45 MPa)	59	°C	ISO 75-1/-2
Vicat softening temperature A	103	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Film Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus, parallel	260	MPa	ISO 527-3
Tensile Modulus, normal	250	MPa	ISO 527-3
Stress at Yield, parallel	14	MPa	ISO 527-3
Stress at Yield, normal	14	MPa	ISO 527-3
Strain at Yield, parallel	16	%	ISO 527-3
Strain at Yield, normal	14	%	ISO 527-3
Stress at Break, parallel	37	MPa	ISO 527-3
Stress at Break, normal	41	MPa	ISO 527-3
Maximum strain, parallel	850	%	ISO 527-3
Maximum strain, normal	900	%	ISO 527-3
Type of extrusion	cast	-	-
Thickness of specimen	0.05	mm	-

Optical Properties	Value	Unit	Test Standard
ASTM Data			
Gloss	92	-	ASTM D 2457
Haze	0.2	%	ASTM D 1003

Characteristics

Processing

Film Extrusion

Features

Heat Sealable

Certifications

Food approval, Food approval 1935/2004/EC, Food approval 10/2011, Food Contact (FDA)

Applications

Packaging

Disclaimer

Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.