

ECOZEN® T110

Copolyester

SK Chemicals

ECOZEN® is a glycol-modified polyethylene terephthalate (PETG) with exceptional transparency and chemical resistance.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0035	mm/mm	ASTM D 955
Density, 73 °F	1270	kg/m ³	ASTM D 792

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield stress	49	MPa	ISO 527
Yield strain	5.7	%	ISO 527
Stress at Break	48	MPa	ISO 527
Strain at Break	150	%	ISO 527
Flexural Modulus (23 °C)	1800	MPa	ISO 178
Flexural strength	73	MPa	ISO 178
Notched Impact Strength (Izod), 23 °C	93	kJ/m ²	ISO 180/1A

ASTM Data			
Tensile Strength at Yield	51	MPa	ASTM D 638
Tensile Strength at Break	53	MPa	ASTM D 638
Elongation at Yield	6.8	%	ASTM D 638
Elongation at Break	200	%	ASTM D 638
Flexural Modulus	1913	MPa	ASTM D 790
Flexural Strength	80.4	MPa	ASTM D 790
Rockwell Hardness	R 119	-	ASTM D 785
Notched Impact Strength (Izod), 1/8 in	860	J/m	ASTM D 256

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	81	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	97	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	99	°C	ASTM D 648
DTUL @ 264 psi	85	°C	ASTM D 648

Optical Properties	Value	Unit	Test Standard
ASTM Data			
Haze	1	%	ASTM D 1003
Light Transmittance	86	%	ASTM D 1003

Characteristics

Processing

Sheet Extrusion

Chemical Resistance

General Chemical Resistance

Special Characteristics

Heat aging stabilized, Transparent

Certifications

Contains renewable resources, Food approval

Features

Copolymer

Applications

Packaging

Disclaimer

Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS'

internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.