

Version: SK-161222  
Date Updated: 2018-10-16

**Technical Data Sheet****SKYPEL G163D****DESCRIPTION**

SKYPEL G163D is a thermoplastic polyester elastomer resin with a medium 63D hardness based on shore D scale is widely used for injection molding and extrusion applications.

**Physical properties**

Properties	ASTM No	Units	G163D
Hardness	D2240	Shore D	63
Specific Gravity	D792	-	1.21
Water Absorption, 24hr	D570	%	0.3
Mold Shrinkage	D955	%	1.5
Tensile Stress at 5% Strain <sup>1)</sup>	D638	kgf/cm <sup>2</sup>	110
Tensile Stress at 10% Strain <sup>1)</sup>	D638	kgf/cm <sup>2</sup>	175
Tensile Stress at Break <sup>1)</sup>	D638	kgf/cm <sup>2</sup>	440
Elongation at Break <sup>1)</sup>	D638	%	500
Flexural Modulus <sup>2)</sup>	D790	kgf/cm <sup>2</sup>	3200
Tear Strength <sup>3)</sup>	D1004	kN/m	180
Izod Impact Strength / Notched <sup>4)</sup>	D256	kg·cm/cm	N.B.
Resilience <sup>5)</sup>	D2632	%	53
Melting Point <sup>6)</sup>	D3418	°C	212
Heat Distortion Temperature <sup>7)</sup>	D648	°C	130
Melt Flow Rate	D1238	g/10min	14
- Temperature, °C / 2.16kg		°C	230

1) ASTM Type IV dumbbells diecut from injection molded slab 2mm thick. Crosshead speed 50mm/min.

2) Crosshead speed 1.3mm/min.

3) Specimens 2mm thick. Crosshead speed 51mm/min.

4) Specimens 6.35mm thick. 'N.B.' means 'not broken'

5) Vertical rebound.

6) Differential Scanning Calorimeter (DSC), peak of endotherm. Heating rate 10°C/min.

7) Load 4.6kg/cm<sup>2</sup>.

**PROCESSING**

SKYPEL G163D should be sufficiently dried prior to processing. For effective drying using dehumidifying dryer, it should be held for 2 to 3 hours at 100 °C or overnight at least 70 °C. Pre-dried SKYPEL G163D in aluminum bag is also available for your convenience upon your choice.

**General purpose processing condition**

Process condition				G163D
Injection	Cylinder	Rear Center Front	°C	220 230 230
	Nozzle		°C	235
	Mold		°C	40
Extrusion	Cylinder	Rear Center Front	°C	210 220 225
	Die		°C	225
	Melt		°C	230

*All data reported here are believed to be correct. However, this should not be accepted as a guarantee of their accuracy.*