

Hostalen CRP 100 RCD BLACK (PE-HD)

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	0.23	g/10min	ISO 1133
MFI temperature	190	°C	-
MFI load	5	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1100	MPa	ISO 527
Yield stress	23	MPa	ISO 527
Yield strain	9	%	ISO 527
Strain at Break	650	%	ISO 527
Tensile Creep Modulus, 1h	850	MPa	ISO 899-1
Notched Impact Strength (Charpy), +23°C	26	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	13	kJ/m ²	ISO 179/1eA
Shore Hardness D (15s)	63	-	ISO 868

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	129	°C	ISO 11357-1/-3
Vicat softening temperature, 50°C/h 50N	74	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	958	kg/m ³	ISO 1183
Bulk density	580	kg/m ³	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	190 - 230	°C	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Melt temperature	190 - 230	°C	-

Characteristics

Processing

Injection Molding, Sheet Extrusion, Compression Molding, Pipe/Tube Extrusion

Delivery form

Pellets, Black

Special Characteristics

UV stabilized

Features

Creep Resistance, Thermal Stability, Weldable

Chemical Resistance

General Chemical Resistance, Environmental Stress Crack Resistance, Hydrolysis

Certifications

Food approval, Water contact

Applications

Building Construction

Disclaimer

Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS'

internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.