

Kalix® 2955 BK 000
PA610-GF55

Syensqo

Rheological properties	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
Molding shrinkage, normal	0.3	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	17800	MPa	ISO 527
Tensile Strength	222	MPa	ISO 527
Strain at Break	2.5	%	ISO 527
Flexural Modulus (23°C)	15800	MPa	ISO 178
Notched Impact Strength (Izod), 23°C	20	kJ/m²	ISO 180/1A
Impact Strength (Izod), 23°C	87	kJ/m²	ISO 180/1U

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	214	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	222	°C	ISO 75-1/-2
Burning Behav. at thickness h	HB	class	UL 94
Thickness tested	0.6	mm	-
ASTM Data			
Glass Transition Temperature	55	°C	ASTM E 1356

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1580	kg/m³	ISO 1183
Biobased carbon content	27	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 12	h	-
Processing humidity	≤0.09	%	-
Melt temperature	280 - 330	°C	-
Mold temperature	50 - 130	°C	-
Zone 1	265 - 300	°C	-
Zone 2	280 - 330	°C	-
Zone 3	280 - 330	°C	-

Characteristics
Processing

Injection Molding

Features

Low Warpage

Delivery form

Pellets, Black

Certifications

Contains renewable resources

Special Characteristics

Platable, Impact modified

Applications

Electrical and Electrical

Disclaimer
Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.