

Luran® ECO 358N BC70
SAN

INEOS Styrolution

Luran® ECO 358N BC70 is the general purpose easy-flow grade of SAN, suitable for moldings with very thin walls and / or adverse flow length to wall ratio. It features very good transparency and a light intrinsic color. Luran® ECO 358N BC70 is an ISCC compliant product leading to a substitution of fossil source styrene with ISCC certified bio-attributed styrene.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	22	cm ³ /10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3700	MPa	ISO 527
Stress at Break	72	MPa	ISO 527
Strain at Break	3	%	ISO 527
Impact Strength (Charpy), +23°C	16	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy), -30°C	16	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	2	kJ/m ²	ISO 179/1eA
Flexural Modulus (23°C)	3600	MPa	ISO 178
Flexural strength	120	MPa	ISO 178
Notched Impact Strength (Izod), 23°C	2	kJ/m ²	ISO 180/1A
Ball Indentation Hardness	165	MPa	ISO 2039-1

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	86	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	99	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	106	°C	ISO 306
Coeff. of Linear Therm. Expansion, parallel	70	E-6/K	ISO 11359-1/-2
ASTM Data			
Thermal Conductivity, solid state	0.17	W/(m K)	DIN 52612-1

Other Properties	Value	Unit	Test Standard
ISO Data			
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1080	kg/m ³	ISO 1183
Bulk density	600	kg/m ³	-


Rheological calculation properties	Value	Unit	Test Standard
ISO Data			
Thermal Conductivity of Melt	0.17	W/(m K)	-

Optical Properties	Value	Unit	Test Standard
ASTM Data			
Index of Refraction	1.57	-	ISO 489


Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	220 - 260	°C	-
Mold temperature	40 - 80	°C	-
Injection speed	200	mm/s	-

Diagrams


Viscosity-shear rate




Shearstress-shear rate




Stress-strain




Secant modulus-strain




Stress-strain (isochronous) 23°C




Creep modulus-time 23°C




Stress-strain (isochronous) 40°C




Creep modulus-time 40°C




Stress-strain (isochronous) 60 °C




Creep modulus-time 60 °C




Stress-strain (isochronous) 80 °C




Creep modulus-time 80 °C



Specific volume-temperature (pvT)



Tensile Modulus-Temperature



Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Heat aging stabilized, Transparent

Chemical Resistance

General Chemical Resistance

Certifications

Contains renewable resources, Food approval, ISCC Plus

Applications

General Purpose, Packaging

Injection Molding

PREPROCESSING

Pre-drying, Temperature: 80 °C

Pre-drying, Time: 2 - 4h

PROCESSING

Melt temperature, range: 220 - 260 °C

Mold temperature, range: 40 - 80 °C

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass) (23 °C)
- ✓ Citric Acid solution (10% by mass) (23 °C)
- ✓ Lactic Acid (10% by mass) (23 °C)
- ✓ Hydrochloric Acid (36% by mass) (23 °C)
- ✓ Sulfuric Acid (38% by mass) (23 °C)
- ✓ Sulfuric Acid (5% by mass) (23 °C)
- ✓ Chromic Acid solution (40% by mass) (23 °C)

Bases

- ✓ Sodium Hydroxide solution (35% by mass) (23 °C)
- ✓ Sodium Hydroxide solution (1% by mass) (23 °C)
- ✓ Ammonium Hydroxide solution (10% by mass) (23 °C)

Alcohols

- ✓ Methanol (23 °C)

- ✓ Ethanol (23°C)

Hydrocarbons

- ✓ iso-Octane (23°C)

Standard Fuels

- ✓ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)

Salt solutions

- ✓ Sodium Chloride solution (10% by mass) (23°C)
- ✓ Sodium Hypochlorite solution (10% by mass) (23°C)
- ✓ Sodium Carbonate solution (20% by mass) (23°C)
- ✓ Sodium Carbonate solution (2% by mass) (23°C)
- ✓ Zinc Chloride solution (50% by mass) (23°C)

Other

- ✓ Hydrogen peroxide (23°C)
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
- ✓ Water (23°C)

Disclaimer

Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.