

Luran® S 778TE
ASA

INEOS Styrolution

Luran® S 778TE acrylonitrile styrene acrylate (ASA) polymer features high surface quality and good impact strength including enhanced colour fastness. The product delivers superior long-term performance when exposed to UV irradiation and additionally provide excellent chemical resistance. Luran® S 778TE is an extrusion grade with enhanced heat resistance and best chemical resistance among the Luran® S grades.

流变性能	数值	单位	试验方法
ISO数据			
熔体体积流动速度, MVR	5	cm³/10min	ISO 1133
温度	220	°C	-
载荷	10	kg	-


机械性能	数值	单位	试验方法
ISO数据			
拉伸模量	2500	MPa	ISO 527
屈服应力	54	MPa	ISO 527
屈服伸长率	3.4	%	ISO 527
名义断裂伸长率	8	%	ISO 527
无缺口简支梁冲击强度, +23°C	220	kJ/m²	ISO 179/1eU
简支梁缺口冲击强度, +23°C	15	kJ/m²	ISO 179/1eA
简支梁缺口冲击强度, -30°C	4	kJ/m²	ISO 179/1eA

热性能	数值	单位	试验方法
ISO数据			
热变形温度, 1.80 MPa	103	°C	ISO 75-1/-2
热变形温度, 0.45 MPa	106	°C	ISO 75-1/-2
维卡软化温度, 50°C/h 50N	104	°C	ISO 306
1.5mm名义厚度时的燃烧性	HB	class	UL 94
测试用试样的厚度	1.5	mm	-


其它性能	数值	单位	试验方法
ISO数据			
吸水性	1.65	%	类似ISO 62
吸湿性	0.35	%	类似ISO 62
密度	1070	kg/m³	ISO 1183

函数


动态剪切模量 - 温度




应力 - 应变.




正割模量 - 应变.




应力 - 应变(等时的) 23°C




蠕变模量 - 时间. 23°C




应力 - 应变(等时的) 60°C




蠕变模量 - 时间. 60°C



比容 - 温度(pvT)



拉伸模量 - 温度



特征

加工方法

异型材挤出成型, 片材挤出成型, 其它挤出成型, 热成型

供货形式

粒料

特殊性能

经光稳处理的/耐光的, 经耐紫外线处理的/耐气候的,
经热稳处理的/耐热的

注塑

其它挤出成型

PREPROCESSING

Pre-drying, Temperature: 80°C

Pre-drying, Time: 2 - 4h

PROCESSING

Extrusion, Pipes, Melt temperature: 200 - 240°C

E尾募烦毗尚

PREPROCESSING

Pre-drying, Temperature: 80°C

Pre-drying, Time: 2 - 4h

PROCESSING

Extrusion, Profiles, Melt temperature: 240°C

板材挤出成型

PREPROCESSING

Pre-drying, Temperature: 80°C

Pre-drying, Time: 2 - 4h

PROCESSING

Extrusion, Plates, Melt temperature: 210 - 250°C

耐化学性

酸类

- ✓ 醋酸 (5g/100g) (23°C)
- ✓ 柠檬酸溶液 (10g/100g) (23°C)
- ✓ 乳酸 (10g/100g) (23°C)

- ✓ 盐酸 (36g/100g) (23°C)
- ✓ 硝酸 (40g/100g) (23°C)
- ✓ 硫酸 (38g/100g) (23°C)
- ✓ 硫酸 (5g/100g) (23°C)
- ✓ 铬酸溶液 (40g/100g) (23°C)

碱类

- ✓ 氢氧化钠溶液 (35g/100g) (23°C)
- ✓ 氢氧化钠溶液 (1g/100g) (23°C)
- ✓ 氨水(氢氧化铵) (10g/100g) (23°C)

醇类

- ✓ 异丙醇 (23°C)
- ✓ 甲醇 (23°C)
- ✓ 乙醇 (23°C)

碳氢化合物

- ✓ 正乙烷 (23°C)
- ✓ 异辛烷 (23°C)

矿物油

- ✓ SAE 10W40号多效润滑油 (23°C)

盐溶液

- ✓ 氯化钠溶液(10g/100g) (23°C)
- ✓ 次氯化钠溶液 (10g/100g) (23°C)
- ✓ 碳酸钠溶液 (20g/100g) (23°C)
- ✓ 氯化锌溶液 (50g/100g) (23°C)

其它

- ✓ 水 (23°C)

权利义务的法律声明

权利义务的法律声明

以上所示所有数据均由材料的生产厂家测试得出并提供，物性表所示数据均为参考值，仅具有表证性，不能作为具有约束力的最小或最大局限值。用于测试的样条均为符合规范的标准样条，所得数据会受到着色，模具设计以及生产工艺的影响而发生变化。并且这些数据均由M-Base数据技术公司直接从生产厂家的物性表上拷备而来。因此，本公司以及M-Base均不能保证这些数据的准确性。

我们向客户以口头，书面或通过测试提供的，包括且不局限于产品的化学性能及物理性能，产品应用建议等，都是基于我们所掌握的知识领域诚实提供。不能免除每个客户须通过对所选材料进行测试与检测，以确定该产品的性能适用于其应用，并对材料的选定，确定其性能是否适用于其特定产品，以及其生产工艺负责。同时，该客户必须遵守相关法规及当地政府所定规章制度。针对材料在特定产品上的应用，例如且不仅限于安全关键部件或系统上的适用性，本公司不做任何明确的，或具有暗示性的材料推荐或承诺。

医疗保健方面的应用: 本公司在向客户供应医用，药用及用于诊断的医疗产品之前，必须依据本公司内部所定风险管理准则对其应用做出评估，即便此产品在常规上已被视作适用于医疗保健方面的应用。

重要 - 本公司原则上拒绝以下所有医用，药用或用于诊断的医疗产品

- 依据欧盟医疗器械指令EU directive 93/42/EEC 被划分为危险等级3的医疗产品
 - 移入体内的并且在体内停留时间超过30天的医疗产品
 - 用于医疗器械的具有维持生命或延长生命的关键部件
- 请注意，本公司通用销售及交货条款在任何时间均有效。