

# Makrolon® FR6005

## PC FR

Covestro Deutschland AG

- MVR (300 °C/1.2 kg) 9.0 cm³/10 min
- medium viscosity
- easy release
- flame retardant
- impact modified
- good surface quality
- electrical/electronic
- housing parts

Rheological properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	9	cm³/10min	ISO 1133
Temperature	300	°C	-
Load	1.2	kg	-

Mechanical Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2300	MPa	ISO 527
Yield stress	62	MPa	ISO 527
Yield strain	6	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Puncture - maximum force, +23°C	5100	N	ISO 6603-2
Puncture - maximum force, -30°C	6100	N	ISO 6603-2
Puncture energy, +23°C	54	J	ISO 6603-2
Puncture energy, -30°C	55	J	ISO 6603-2
Flexural Modulus (23°C)	2400	MPa	ISO 178
Flexural strength	90	MPa	ISO 178
Notched Impact Strength (Izod), 23°C	60	kJ/m²	ISO 180/1A
Notched Impact Strength (Izod)	15	kJ/m²	ISO 180/1A
Temperature	-30	°C	-

Thermal Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load (1.80 MPa)	121	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	136	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	142	°C	ISO 306
Coeff. of Linear Therm. Expansion, parallel	70	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	70	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	V-0	class	UL 94
Thickness tested	1.0	mm	-
Glow Wire (GWFI, Flammability Index)	850	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1	mm	-
Glow Wire (GWFI, Flammability Index)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	1.5	mm	-
Glow Wire (GWFI, Flammability Index)	960	°C	IEC 60695-2-12
GWFI - thickness tested (3)	3	mm	-
Glow Wire Ignition Temperature)	875	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1	mm	-
Glow Wire Ignition Temperature)	850	°C	IEC 60695-2-13
GWIT - thickness tested (2)	1.5	mm	-
Glow Wire Ignition Temperature)	900	°C	IEC 60695-2-13
GWIT - thickness tested (3)	3	mm	-

Electrical Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	>1E15	Ohm	IEC 62631-3-2
Comparative tracking index	200	-	IEC 60112

Other Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Density	1200	kg/m³	ISO 1183

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
Injection Molding, melt temperature	300	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	2 - 3	h	-
Processing humidity	≤0.02	%	-
Melt temperature	280 - 320	°C	-
Mold temperature	80 - 120	°C	-
Zone 1	250 - 260	°C	-
Zone 2	270 - 280	°C	-
Zone 3	280 - 290	°C	-
Nozzle temperature	290 - 300	°C	-
Back pressure	5 - 15	MPa	-

## Characteristics

### Processing

Injection Molding

### Special Characteristics

Flame retardant, Impact modified, Transparent

### Delivery form

Black

### Applications

Electrical and Electronical, Encapsulation

### Additives

Release agent

## Disclaimer

### Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

**Healthcare uses:** the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

**Important:** irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.