

Product Data Sheet

SUPRENE[®] 537-3

SUPRENE[®] 537-3

SUPRENE EPDM 537-3 is used by blending with IIR.

SUPRENE EPDM 537-3 shows excellent heat aging properties, especially with peroxide cures.

It blends easily in all formulation and gives excellent weathering and low temperature impact properties.

SUPRENE EPDM 537-3 is mainly used in blends with IIR for inner tubes.
It can also be used in various applications such as mechanical goods.

Raw Polymer Properties

	Test Method	Unit	Min.	Max.	Typical Value
Mooney Viscosity, (ML 1+4, 125 °C unmilled)	ASTM D1646	-	30	40	35
Ethylene Content	ASTM D3900	wt%	54	60	57
ENB Content	ASTM D6047	wt%	1.8	2.8	2.3
Oil Content	-	phr	-	-	-
Specific Gravity	ASTM D792	-	-	-	0.86
Volatile Matter	ASTM D5668	wt%	-	0.8	-
Ash	ASTM D5667	wt%	-	0.15	-
Physical Form, (kg/bale)	-	-	-	-	25kg (Dense Bale)

* Ethylene Content + Propylene Content = 100%

SUPRENE[®] 537-3

Typical Properties

Properties	Test Method	S537-3
Mooney Viscosity ML 1+4 @ 125°C	ASTM D1646	35.0
Ethylene Content, wt%	ASTM D3900	57.0
ENB Content, wt%	ASTM D6047	2.3

Guide Formulation

Formulation 1 (IIR Blend)

Formulation 1	
S537-3	18.0
IIR(BK1675N)	82.0
HAF	40.0
GPF	35.0
P-4W	35.0
CIR	5.0
ZnO	4.0
Stearic Acid	1.0
MBT(M)	0.5
TMTD(TT)	1.0
Sulfur	1.5
Total	223.0

* Unit: phr

Properties	Test Method	Formulation 1
Compound Mooney Viscosity ML 1+4 @ 100°C	ASTM D1646	66.4
Pre-vulcanization characteristics Large Rotor at 125°C	ASTM D1646	
Minimum Viscosity (Vm)		36.8
t'5 (min)		17.75
t'35 (min)		25.18
Δt30		7.43
Rotorless Cure Meter (MDR, 160°C/30min)	ASTM D5289	
M _L (lb·in)		2.0
M _H (lb·in)		13.1
t _{S2} (min)		2.80
t _{C50} (min)		4.22
t _{C90} (min)		15.46

Cured at 160°C for 20 min

Properties	Test Method	Formulation 1
Specific Gravity	ASTM D792	1.12
Hardness (shore A)	ASTM D2240	64
Tensile Strength (kgf/cm ²)	ASTM D412	111
Elongation (%)	ASTM D412	562
100% Modulus (kgf/cm ²)	ASTM D412	19.1

Heat Resistance

Properties	Test Method	Formulation 1
Hardness (Change Point)	ASTM D2240	+6
Tensile Strength (Change %)	ASTM D412	-22
Elongation (Change %)	ASTM D412	-27

* After 72 hours oven aging at 120 °C per ASTM D573

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.

Formulation 2

Formulation 2	
S537-3	100.0
CaCO ₃	120.0
P-4W	40.0
RD	1.5
SR-350	1.0
DCP-40PD	7.0
Total	269.5

* Unit: phr

Properties	Test Method	Formulation 2
Compound Mooney Viscosity ML 1+4 @ 100°C	ASTM D1646	44.6
Pre-vulcanization characteristics Large Rotor at 125°C	ASTM D1646	
Minimum Viscosity (Vm)		26.8
t'5 (min)		7.88
t'35 (min)		145.07
Δt30		137.19
Rotorless Cure Meter (MDR, 160°C/30min)	ASTM D5289	
M _L (lb·in)		1.5
M _H (lb·in)		16.6
t _{s2} (min)		1.44
t _{c50} (min)		5.05
t _{c90} (min)		18.50

Cured at 160°C for 20 min

Properties	Test Method	Formulation 2
Specific Gravity	ASTM D792	1.25
Hardness (shore A)	ASTM D2240	55
Tensile Strength (kgf/cm ²)	ASTM D412	53
Elongation (%)	ASTM D412	836
100% Modulus (kgf/cm ²)	ASTM D412	11.5

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Global Chemical's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Global Chemical's invoices and/or order acknowledgments. Except as expressly provided in SK Global Chemical's standard terms and conditions of sale, SK Global Chemical and its affiliates make no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Global Chemical and its affiliates assume no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes.

The **Innovative Chemical** Company

“
The global chemical company that never stops its transformation to build the best-ever chemical portfolio.
SK global chemical creates the new future of the chemical industry toward its customers and markets.

The general energy and chemical leader in the global market,
SK global chemical



SK global chemical Co., Ltd. 26, Jong-ro, Jongno-gu, Seoul, Korea

TEL +82-2-2121-5114 FAX +82-2-2121-7001

© 2016 SK global chemical Co., Ltd