

Ultradur® B 4030 G6
PBT-GF30

BASF

Impact-modified injection-molding grade with 30% glass fibers for technical parts; rigid, tough and dimensionally stable; for example in housings and connectors in the engine compartment.

Abbreviated designation according to ISO 1043: PBT-GF30

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	2.2	cm³/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	9200	MPa	ISO 527
Stress at Break	125	MPa	ISO 527
Strain at Break	3.6	%	ISO 527
Impact Strength (Charpy), +23°C	80	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	83	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	16	kJ/m²	ISO 179/1eA
Ball Indentation Hardness	190	MPa	ISO 2039-1

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	223	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	205	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	25	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	HB	class	UL 94
Thickness tested	1.5	mm	-
Burning Behav. at thickness h	HB	class	UL 94
Thickness tested	0.8	mm	-

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	3.9	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.7	-	IEC 62631-2-1
Dissipation Factor, 100Hz	27	E-4	IEC 62631-2-1
Dissipation Factor, 1MHz	193	E-4	IEC 62631-2-1
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	>1E15	Ohm	IEC 62631-3-2
Electric Strength	39	kV/mm	IEC 60243-1
Comparative tracking index	375	-	IEC 60112

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1480	kg/m³	ISO 1183

Material Specific Properties	Value	Unit	Test Standard
ISO Data			
Viscosity number	105	cm³/g	ISO 307, 1157, 1628


Rheological calculation properties	Value	Unit	Test Standard
ISO Data			
Ejection temperature	170	°C	-

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	250	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.04	%	-
Melt temperature	250 - 275	°C	-
Mold temperature	60 - 100	°C	-

Diagrams

Specific volume-temperature (pvT)



Characteristics

Processing

Injection Molding

Delivery form

Pellets, Black

Additives

Lubricants

Special Characteristics

Impact modified, Light stabilized or stable to light, UV stablized, Heat aging stabilized

Chemical Resistance

Hydrolysis

Applications

Automotive

Injection Molding

PREPROCESSING

Pre/Post-processing, max. allowed water content: .04 %
Pre/Post-processing, Pre-drying, Temperature: 80 - 120 °C
Pre/Post-processing, Pre-drying, Time: 4 h

PROCESSING

injection molding, Melt temperature, range: 250 - 275 °C
injection molding, Melt temperature, recommended: 260 °C
injection molding, Mold temperature, range: 60 - 100 °C
injection molding, Mold temperature, recommended: 80 °C

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass) (23°C)

Disclaimer

Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.