

**Ultradur® B 4522 PRO**  
PBT

BASF

Rheological properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	20	cm³/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.5	%	ISO 294-4, 2577
Molding shrinkage, normal	1.7	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	55	MPa	ISO 527
Yield strain	3.7	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Tensile Creep Modulus, 1000h	1200	MPa	ISO 899-1
Impact Strength (Charpy), +23°C	no break	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	240	kJ/m²	ISO 179/1eU
Type of failure	C	-	-
Notched Impact Strength (Charpy), +23°C	4	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	3.5	kJ/m²	ISO 179/1eA
Flexural Modulus (23°C)	2400	MPa	ISO 178
Flexural strength	85	MPa	ISO 178
Ball Indentation Hardness	130	MPa	ISO 2039-1
<b>ASTM Data</b>			
Notched Impact Strength (Izod), 1/8 in	50	J/m	ASTM D 256

Thermal Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting Temperature (10°C/min)	223	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	65	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	165	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	110	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	110	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	HB	class	UL 94
Thickness tested	1.5	mm	-
Burning Behav. at thickness h	HB	class	UL 94
Thickness tested	0.8	mm	-
UL recognition	yes	-	-
Oxygen index	20	%	ISO 4589-1/-2
Glow Wire (GWFI, Flammability Index)	850	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1.5	mm	-
Glow Wire Ignition Temperature)	775	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1.5	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	3	mm	-
Thermal Conductivity, solid state	0.27	W/(m K)	DIN 52612-1
Specific Heat	1250	J/(kg K)	

Electrical Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 100Hz	3.4	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.3	-	IEC 62631-2-1
Dissipation Factor, 100Hz	20	E-4	IEC 62631-2-1
Dissipation Factor, 1MHz	200	E-4	IEC 62631-2-1
Volume Resistivity	1E14	Ohm*m	IEC 62631-3-1
Surface Resistivity	1E13	Ohm	IEC 62631-3-2
Electric Strength	36	kV/mm	IEC 60243-1
Comparative tracking index	550 <sup>[1]</sup>	-	IEC 60112

1: Test liquid A

Other Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Water Absorption	0.5	%	Sim. to ISO 62
Humidity absorption	0.25	%	Sim. to ISO 62
Density	1300	kg/m³	ISO 1183
Bulk density	750	kg/m³	-
<b>Material Specific Properties</b>			
<b>ISO Data</b>			
Viscosity number	130	cm³/g	ISO 307, 1157, 1628
<b>Processing Recommendation Injection Molding</b>			
Melt temperature	250 - 275	°C	-
Mold temperature	40 - 70	°C	-
<b>Processing Recommendation Extrusion</b>			
Melt temperature	250 - 275	°C	-

## Characteristics

### Processing

Injection Molding, Other Extrusion

### Applications

Automotive, Medical

### Certifications

Medical, Biocompatibility ISO 10993, US Pharmacopeia Class VI  
Approved, Drug Master File, Food approval, Food approval  
10/2011, Food Contact (FDA)

## Disclaimer

### Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

**Healthcare uses:** the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

**Important:** irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.