

**Ultradur® B 6550 LN FC**  
**PBT**

BASF

Ultradur® B6550LN FC UN is suitable for plastic parts, where material approval regarding drinking water contact and direct food contact is a mandatory requirement.

The product is approved according to

- 21 CFR FDA §177.1660 "Poly(tetramethylene terephthalate)";
- European Food Contact European Food Contact Commission Regulation (EU) 10/2011;
- GMP (EC) N°2023/2006

For questions regarding the compliance with further regulations, and certificates, please contact your local BASF representative or Plastics Safety (E-Mail: [plastics.safety@basf.com](mailto:plastics.safety@basf.com)).

The products can also be offered as BMBcert™ and/or Ccycled™. Due to the Massbalance approach the product properties do not change.

Rheological properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	9.5	cm³/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2600	MPa	ISO 527
Yield stress	56	MPa	ISO 527
Yield strain	3.5	%	ISO 527
Nominal strain at break	>50	%	ISO 527
Impact Strength (Charpy), +23°C	no break	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	220	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	5	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	5	kJ/m²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting Temperature (10°C/min)	223	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	50	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	135	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	115	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	115	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	HB	class	UL 94
Thickness tested	1.5	mm	-
Burning Behav. at thickness h	HB	class	UL 94
Thickness tested	0.8	mm	-

Electrical Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 100Hz	3.4	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
Dissipation Factor, 100Hz	19	E-4	IEC 62631-2-1
Dissipation Factor, 1MHz	219	E-4	IEC 62631-2-1
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	1E13	Ohm	IEC 62631-3-2
Electric Strength	39	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112

Other Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Water Absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.25	%	Sim. to ISO 62
Density	1300	kg/m³	ISO 1183


Material Specific Properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Viscosity number	160	cm³/g	ISO 307, 1157, 1628

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
Injection Molding, melt temperature	260	°C	ISO 294
Injection Molding, mold temperature	60	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.04	%	-
Melt temperature	260 - 270	°C	-
Mold temperature	40 - 80	°C	-

## Diagrams

### Coeff. of linear thermal expansion, normal



## Characteristics

### Processing

Injection Molding, Film Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion

### Certifications

Food approval, Food approval 10/2011, Food Contact (FDA)

### Delivery form

Pellets

### Injection Molding

#### PREPROCESSING

Pre/Post-processing, max. allowed water content: .04 %  
Pre/Post-processing, Pre-drying, Temperature: 80 - 120 °C  
Pre/Post-processing, Pre-drying, Time: 4 h

#### PROCESSING

injection molding, Melt temperature, range: 260 - 270 °C  
injection molding, Melt temperature, recommended: 260 °C  
injection molding, Mold temperature, range: 40 - 80 °C  
injection molding, Mold temperature, recommended: 60 °C

### Other Extrusion

#### PREPROCESSING

Pre/Post-processing, max. allowed water content: .04 %

Pre/Post-processing, Pre-drying, Temperature: 80 - 120 °C  
Pre/Post-processing, Pre-drying, Time: 4 h

**PROCESSING**

Extrusion, Prepreg, Melt temperature: 250 - 270 °C  
Extrusion, Pipes, Melt temperature: 250 - 270 °C  
Extrusion, cable sheathing, Melt temperature: 260 - 270 °C

**Profile extrusion**

**PREPROCESSING**

Pre/Post-processing, max. allowed water content: .04 %  
Pre/Post-processing, Pre-drying, Temperature: 80 - 120 °C  
Pre/Post-processing, Pre-drying, Time: 4 h

**PROCESSING**

Extrusion, Profiles, Melt temperature: 250 - 270 °C

**Sheet Extrusion**

**PREPROCESSING**

Pre/Post-processing, max. allowed water content: .04 %  
Pre/Post-processing, Pre-drying, Temperature: 80 - 120 °C  
Pre/Post-processing, Pre-drying, Time: 4 h

**PROCESSING**

Extrusion, Plates, Melt temperature: 250 - 270 °C

**Chemical Media Resistance**

**Acids**

✓ Acetic Acid (5% by mass) (23°C)

**Disclaimer**

**Liability Exclusion**

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

**Healthcare uses:** the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

**Important:** irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.