

Ultramid® A3EG7 FC Aqua UN
PA66-GF35

BASF

Ultramid® A3EG7FC Aqua UN is optimized for plastic parts, mandatory requiring material approvals for drinking water or direct food contact. The product is approved according to

- 21 CFR FDA § 177.1500 "Nylon resins". (for repeated use applications only)
- European Food Contact European Food Contact Commission Regulation (EU) 10/2011
- GMP (EC) n° 2023/2006

and provides the approvals for drinking water regulations of

- KTW
- DVGW W270
- WRAS
- ACS (disclosure of ingredients)
- NSF (disclosure of ingredients)

For questions regarding the compliance with further regulations, and certificates, please contact your local BASF representative or Plastics Safety (E-Mail: plastics.safety@basf.com).

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	35 / *	cm ³ /10min	ISO 1133
Temperature	275 / *	°C	-
Load	5 / *	kg	-
Molding shrinkage, parallel	0.5 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0 / *	%	ISO 294-4, 2577

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	11500 / 8500	MPa	ISO 527
Stress at Break	210 / 150	MPa	ISO 527
Strain at Break	3 / 5	%	ISO 527
Tensile Creep Modulus, 1000h	* / 6650	MPa	ISO 899-1
Impact Strength (Charpy), +23°C	95 / 105	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy), -30°C	75 / -	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	14 / 22	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	12 / -	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Izod), 23°C	14 / 18	kJ/m ²	ISO 180/1A


Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	250 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	250 / *	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	250 / *	°C	ISO 306
Coeff. of Linear Therm. Expansion, parallel	22 / *	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	93 / *	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	HB / *	class	UL 94
Thickness tested	1.6 / *	mm	-
UL recognition	yes / *	-	-
Burning Behav. at thickness h	HB / *	class	UL 94
Thickness tested	0.8 / *	mm	-
UL recognition	yes / *	-	-
Oxygen index	24 / *	%	ISO 4589-1/-2

Electrical Properties	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.5 / 5.7	-	IEC 62631-2-1
Dissipation Factor, 100Hz	200 / 3000	E-4	IEC 62631-2-1
Dissipation Factor, 1MHz	200 / 1500	E-4	IEC 62631-2-1
Volume Resistivity	>1E13 / 1E11	Ohm*m	IEC 62631-3-1
Surface Resistivity	* / 1E10	Ohm	IEC 62631-3-2
Electric Strength	40 / 37	kV/mm	IEC 60243-1
Comparative tracking index	- / 550	-	IEC 60112


Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Water Absorption	5 / *	%	Sim. to ISO 62
Humidity absorption	1.6 / *	%	Sim. to ISO 62
Density	1410 / -	kg/m³	ISO 1183
Bulk density	700	kg/m³	-
Material Specific Properties			
ISO Data			
Viscosity number	145 / *	cm³/g	ISO 307, 1157, 1628
Rheological calculation properties			
ISO Data			
Ejection temperature	195	°C	-
Test specimen production			
ISO Data			
Injection Molding, melt temperature	290	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.15	%	-
Melt temperature	280 - 300	°C	-
Mold temperature	80 - 90	°C	-

Diagrams


Viscosity-shear rate




Shearstress-shear rate




Dynamic Shear modulus-temperature




Dynamic Shear modulus-temperature




Stress-strain




Stress-strain




Secant modulus-strain




Secant modulus-strain




Stress-strain (isochronous) 23 °C




Creep modulus-time 23 °C




Stress-strain (isochronous) 60 °C




Creep modulus-time 60 °C




Stress-strain (isochronous) 90 °C




Creep modulus-time 90 °C




Stress-strain (isochronous) 120°C




Creep modulus-time 120°C




Stress-strain (isochronous) 140°C




Creep modulus-time 140°C




Specific volume-temperature (pvT)



Tensile Modulus-Temperature



Tensile Modulus-Temperature



Characteristics

Processing

Injection Molding, Other Extrusion

Delivery form

Pellets, Natural Color

Additives

Lubricants, Release agent

Special Characteristics

Heat aging stabilized

Certifications

Food approval, Food approval 10/2011, Food Contact (FDA),
Water contact, Water contact KTW, Water contact DVGW W270,
NSF Approval

Applications

Automotive

Injection Molding

PREPROCESSING

Pre/Post-processing, max. allowed water content: .15 %

Pre/Post-processing, Pre-drying, Temperature: 80 °C

Pre/Post-processing, Pre-drying, Time: 4 h

PROCESSING

injection molding, Melt temperature, range: 280 - 300 °C
injection molding, Melt temperature, recommended: 290 °C
injection molding, Mold temperature, range: 80 - 90 °C
injection molding, Mold temperature, recommended: 80 °C
injection molding, Dwell time, thermoplastics: 10 min

Disclaimer

Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.