



Ultramid® A3XZC3 ESD bk 23187 PA66-CF15

BASF

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	7 / *	cm ³ /10min	ISO 1133
Temperature	300 / *	°C	-
Load	10 / *	kg	-
Molding shrinkage, parallel	0.5 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	10000 / 5800	MPa	ISO 527
Stress at Break	130 / 85	MPa	ISO 527
Strain at Break	3.7 / 8	%	ISO 527
Impact Strength (Charpy), +23°C	70 / 80	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	70 / -	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	13 / 20	kJ/m²	ISO 179/1eA
Flexural Modulus (23°C)	8000 / 5100	MPa	ISO 178
Flexural strength	180 / 120	MPa	ISO 178

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data	-		
Melting Temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	235 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	255 / *	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	14 / *	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	130 / *	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	V-0 / *	class	UL 94
Thickness tested	1.6 / *	mm	-
Glow Wire (GWFI, Flammability Index)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1	mm	-

Electrical Properties	dry / cond	Unit	Test Standard
ISO Data			
Surface Resistivity	* / 1000000	Ohm	IEC 62631-3-2

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Density	1190 / -	kg/m³	ISO 1183
Bulk density	700	kg/m³	-

Material Specific Properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	180 / *	cm³/g	ISO 307, 1157, 1628

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	280 - 300	°C	-
Mold temperature	80 - 90	°C	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Melt temperature	280 - 300	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Special Characteristics

Flame retardant, Impact modified

Delivery form

Pellets, Black

Disclaimer

Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.