

Ultramid® C3U
PA66/6 FR(30)

BASF

Without halogens and phosphorous flame retardant injection molding grade, used e.g. for impact resistant electrical insulating parts such as contact bases and plug connector strips. Due to the halide free stabilization the impact on corrosion is minimized and sensitive electronic components are better protected.

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	160 / *	cm³/10min	ISO 1133
Temperature	275 / *	°C	-
Load	5 / *	kg	-
Molding shrinkage, parallel	1.2 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.3 / *	%	ISO 294-4, 2577

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	3500 / 1500	MPa	ISO 527
Yield stress	75 / 45	MPa	ISO 527
Yield strain	4 / 20	%	ISO 527
Nominal strain at break	6 / >50	%	ISO 527
Tensile Creep Modulus, 1h	* / 1000	MPa	ISO 899-1
Tensile Creep Modulus, 1000h	* / 890	MPa	ISO 899-1
Impact Strength (Charpy), +23°C	80 / no break	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	6 / 35	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	4 / -	kJ/m²	ISO 179/1eA

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	243 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	70 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	210 / *	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	68 / *	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	81 / *	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	V-0 / *	class	UL 94
Thickness tested	1.6 / *	mm	-
UL recognition	yes / *	-	-
Burning Behav. at thickness h	V-0 / *	class	UL 94
Thickness tested	0.4 / *	mm	-
UL recognition	yes / *	-	-
Oxygen index	34 / *	%	ISO 4589-1/-2


Electrical Properties	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.6 / 6	-	IEC 62631-2-1
Dissipation Factor, 1MHz	200 / 3000	E-4	IEC 62631-2-1
Volume Resistivity	1E13 / 1E9	Ohm*m	IEC 62631-3-1
Surface Resistivity	* / 1E12	Ohm	IEC 62631-3-2
Electric Strength	32 / 28	kV/mm	IEC 60243-1
Comparative tracking index	- / 600	-	IEC 60112

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Water Absorption	8.5 / *	%	Sim. to ISO 62
Humidity absorption	2.9 / *	%	Sim. to ISO 62
Density	1160 / -	kg/m³	ISO 1183


Material Specific Properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	145 / *	cm³/g	ISO 307, 1157, 1628

Rheological calculation properties	Value	Unit	Test Standard
ISO Data			
Density of melt	1010	kg/m³	-


Dynamic Shear modulus-temperature




Stress-strain




Stress-strain




Secant modulus-strain




Secant modulus-strain




Stress-strain (isochronous) 23 °C




Creep modulus-time 23 °C




Stress-strain (isochronous) 90 °C




Creep modulus-time 90 °C




Stress-strain (isochronous) 140 °C




Creep modulus-time 140 °C




Specific volume-temperature (pvT)



Tensile Modulus-Temperature



Tensile Modulus-Temperature



Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Flame retardant, Halogen-free, Heat aging stabilized

Injection Molding

PREPROCESSING

Pre/Post-processing, max. allowed water content: .15 %

Pre/Post-processing, Pre-drying, Temperature: 80 °C

Pre/Post-processing, Pre-drying, Time: 4 h

PROCESSING

injection molding, Melt temperature, range: 250 - 270 °C

injection molding, Melt temperature, recommended: 260 °C

injection molding, Mold temperature, range: 60 - 80 °C

injection molding, Mold temperature, recommended: 70 °C

injection molding, Dwell time, thermoplastics: 10 min

Chemical Media Resistance

Acids

✓ Acetic Acid (5% by mass) (23°C)

Disclaimer

Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.