

Ultramid® Exp.A3U44G6 DC
PA66-GF30

BASF

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	10 / *	cm³/10min	ISO 1133
Temperature	275 / *	°C	-
Load	5 / *	kg	-
Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	11000 / 10900	MPa	ISO 527
Stress at Break	155 / 120	MPa	ISO 527
Strain at Break	3 / 3.2	%	ISO 527
Impact Strength (Charpy), +23°C	70 / 65	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	70 / 60	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	8.5 / 9	kJ/m²	ISO 179/1eA
Flexural Modulus (23°C)	10500 / 9500	MPa	ISO 178
Flexural strength	240 / 195	MPa	ISO 178

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	235 / *	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	23 / *	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	67 / *	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	V-0 / *	class	UL 94
Thickness tested	0.4 / *	mm	-
UL recognition	yes / *	-	-
Glow Wire (GWFI, Flammability Index)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	0.8	mm	-

Electrical Properties	dry / cond	Unit	Test Standard
ISO Data			
Dissipation Factor, 1MHz	115 / 230	E-4	IEC 62631-2-1
Volume Resistivity	1E12 / 1E11	Ohm*m	IEC 62631-3-1
Surface Resistivity	* / 1E15	Ohm	IEC 62631-3-2
Electric Strength	39 / 39	kV/mm	IEC 60243-1
Comparative tracking index	- / 600	-	IEC 60112

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Water Absorption	5.3 / *	%	Sim. to ISO 62
Humidity absorption	1.7 / *	%	Sim. to ISO 62
Density	1430 / -	kg/m³	ISO 1183
Bulk density	700	kg/m³	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	280 - 30	°C	-
Mold temperature	80 - 90	°C	-

Processing Recommendation Extrusion	Value	Unit	Test Standard
Melt temperature	280 - 300	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Features

Color Stability

Delivery form

Pellets

Applications

Electrical and Electronical

Special Characteristics

Flame retardant, Halogen-free

Disclaimer

Liability Exclusion

These guide values are measured and provided by the product manufacturer and have been determined on standardised test specimens and can be affected by pigmentation, mould design and processing conditions. M-Base has taken the guide values from the producer's original Technical Data Sheet. **ALBIS AND M-BASE ARE THEREFORE NOT RESPONSIBLE FOR THE ACCURACY OF THE GUIDE VALUES AND CANNOT GIVE ANY WARRANTY WITH REGARD TO THEIR CORRECTNESS.**

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended.

The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations. **NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO, SAFETY-CRITICAL COMPONENTS OR SYSTEMS.**

Healthcare uses: the supply of any product by ALBIS for any medical, pharmaceutical or diagnostic application is conditional to an assessment by ALBIS in terms of compliance with ALBIS' internal risk management policy – even for products which are in general designated for use in Healthcare applications.

Important: irrespective of product type or designation, ALBIS does not recommend or support the use of any products it supplies which fall into the following medical, pharmaceutical or diagnostic application categories:

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant application for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.