

Technical Data Sheet

LURANYL® KR 2460/3-2



PPE+PS-I Blend with halogen free flame retardant; high GWIT

<i>Properties</i>	<i>Unit</i>	<i>Test Method</i>	<i>Test Conditions</i>	<i>Value*</i>	<i>Remarks</i>
<i>Mechanical</i>					
Tensile Modulus	MPa	ISO 527	23°C 1mm/min	2,900	
Tensile Strength	MPa	ISO 527	23°C 50 mm/min	88	
Elongation at Yield	%	ISO 527	23°C 50 mm/min	15	
Flexural Modulus	MPa	ISO 178	23°C 2 mm/min	3,000	
Impact Strength Notched (Charpy)	kJ/m²	ISO 179/1eA	80 x 10 x 4 mm 23°C	6	
Impact Strength (Charpy)	kJ/m²	ISO 179/1eU	80 x 10 x 4 mm 23°C / -30°C	n.b. / n.b.	
<i>Physical</i>					
Density	g/cm³	ISO 1183	23°C, 50% RH	1.18	
Water Absorption	%	ISO 62	23°C, 24 h	< 0.1	
<i>Thermal</i>					
Heat Distortion Temperature (HDT A)	°C	ISO 75	1.80 MPa	120	
Vicat Softening Temperature (B 50)	°C	ISO 306	50°C/h 50N	155	
Melt Volume Rate MVR	cm³/10 min	ISO 1133	250°C 21.6 kg	10	
Thermal Conductivity	W/(K·m)	DIN 52612	260x260x10 mm	0.20	
Linear Thermal Expansion	10 ⁻⁴ · K ⁻¹	ISO 11359-2	23°C - 80°C	0.4 - 0.5	
Moulding Shrinkage	%	ISO 294-4	23°C 3,2 mm	0.3 - 0.5	
Flammability (own test)	Class	UL 94	1.6 mm	V-0	
Glow Wire Ignition Temperature (GWIT)	°C	IEC 60695-2-13	2,0 mm	775	

* = Average figures which could vary with each production batch due to addition of pigments, antistatic agents, slip agents, light stabilizers or other additives.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors from the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.