

Item	Test Method		Unit	AR-FL-60	AR-FL-75	AR-FL-85
	Characteristic			(3)	(3)	(3)
			-	Low hardness	High elasticity	Good moldability
Hardness	JIS K 6253	typeA	point	60	73	86
Specific Gravity	JIS K 7112		-	0.89	0.9	0.9
Melt Flow Rate	ASTM D 1238	190 × 21.2N	g/10min	27	5	17
Tensile strength	JIS K 6251		MPa	6.4	12	8.1
300%Modulus	"		"	3.1	4.4	4.4
Elongation	"		%	550	730	680
Tear Strength	JIS K 6252		kN/m	24	42	32
Rebound resilience	JIS K 6255		%	48	36	38
Taber abrasion Test	JIS K 6264	H22 × 9.8N × 1000Cycle	mg	471	199	316
Compression Set	JIS K 6262	23 × 24hr	%	25	19	20
		70 × 24hr	"	95	94	80
		100 × 24hr	"	-	-	100
Softening Temperature	our method 1			63	80	84
Brittleness Temperature	JIS K 7216		"	<-50		<-60
Weather resistance	-		-	○		
Mold Shrinkage (Vertical/Flowing directions)	our method 2		%	0.8/1.6	0.6/1.9	1.2/1.7
Molding Method	-		-	Film molding ・ Injection		
Drying	-		-	unnecessary		
Color	-		-	Transparence		Semi-transparent
Haze	JIS K 7136		%	18	49	74
Fusion strength	our method	PP	-	○	○	○
		ABS	-	×	×	×
		PC	-	×	×	×
		PET	-	×	×	×
		6Ny(PA)	-	×	×	×
		PBT	-	×	×	×
		POM	-	×	×	×
		PVC	-	×	×	×

The values shown in the table are representative ones and not guaranteed.
The figures in the table are subject to change without notice.
Reproduction of this information without our consent is prohibited.
1 Softening temperature measurement method: Vicat softening temperature (at temperature rise rate of 50 /hour and load of 2.5N) was determined with a needle inserted by 1mm.
2 Shrinkage : A film gate sheet (126mm x 126mm x 2mm) was formed (at mold temperature of 40 and cooling period of 40 seconds) .

3 This is a grade that is made to order and sold.