

Item	Test Method		Unit	AR-NK-80
	Characteristic		-	Low migration
Hardness	JIS K 6253	typeA	point	80
Specific Gravity	JIS K 7112		-	0.9
Melt Flow Rate	ASTM D 1238	230 × 21.2N	g/10min	12
Tensile strength	JIS K 6251		MPa	17.2
300%Modulus	"		"	5.2
Elongation	"		%	780
Tear Strength	JIS K 6252		kN/m	50
Rebound resilience	JIS K 6255		%	32
Taber abrasion Test	JIS K 6264	H22 × 9.8N × 1000Cycle	mg	81
Compression Set	JIS K 6262	23 × 24hr	%	22
		70 × 24hr		86
Softening Temperature	our method 1			96
Brittleness Temperature	JIS K 7216			<-60
Mold Shrinkage (Vertical/Flowing directions)	our method 2		%	0.3/1.1
Molding Method	-		-	Injection ・ Extrusion
Drying	-		-	unnecessary
Color	-		-	Transparent
Haze	JIS K 7136		%	26
Fusion strength	our method	PP	-	
		ABS	-	×
		PC	-	×
		PET	-	×
		6Ny(PA)	-	×
		PBT	-	×
		POM	-	×
		PVC	-	×

The values shown in the table are representative ones and not guaranteed.
The figures in the table are subject to change without notice.
Reproduction of this information without our consent is prohibited.
1 Softening temperature measurement method: Vicat softening temperature (at temperature rise rate of 50 /hour and load of 2.5N) was determined with a needle inserted by 1mm.
2 Shrinkage : A film gate sheet (126mm x 126mm x 2mm) was formed (at mold temperature of 40 and cooling period of 40 seconds) .
3 This is a grade that is made to order and sold.