

Item	Test Method		Unit	TF-A30NT	TF-A40NT	TF-A50NT	TF-A60NT	TF-A70NT	TF-A80NT	TF-A90NT
	Characteristic		-	Good moldability						
Hardness	JIS K 6253	typeA	point	28	43	50	63	70	80	88
		typeD	＂	-	-	-	-	-	-	29
Specific Gravity	JIS K 7112		-	0.98	0.98	1.00	1.00	1.01	1.01	1.01
Melt Flow Rate	ASTM D 1238	230 × 37.3N	g/10min	25	5.5	4.8	3.3	2.5	9.1	3.8
Tensile strength	JIS K 6251		MPa	4.8	6.7	7.7	9.8	11.6	13.7	15.6
Elongation	JIS K 6251		%	920	830	860	800	810	770	760
Tear Strength	JIS K 6252		kN/m	11	16	18	24	29	39	52
Rebound resilience	JIS K 6255		%	58	57	55	51	47	41	36
Taber abrasion Test	JIS K 6264	H22 × 9.8N × 1000Cycle	mg	980	757	192	199	16	18	43
Compression Set	JIS K 6262	23 × 24hr	%	10	14	16	20	24	26	34
		70 × 24hr	%	27	33	34	34	41	48	53
		100 × 24hr	%	58	59	58	58	60	61	64
Softening Temperature	our method 1			71	73	86	95	117	139	147
Brittleness Temperature	JIS K 7216			<-60	<-60	<-60	<-60	<-60	<-60	<-60
Mold Shrinkage (Vertical/Flowing directions)	our method 2		%	0.4/3.0	0.6/3.1	0.6/2.0	0.6/2.0	0.8/1.9	0.8/1.6	0.9/1.6
Molding Method	-		-	Injection ・ Extrusion						
Drying	-		-	unnecessary						
Color	-		-	Natural ・ Black						
Flame Retardance	UL-94		-	HB equivalent						

The values shown in the table are representative ones and not guaranteed.
The figures in the table are subject to change without notice.
Reproduction of this information without our consent is prohibited.
1 Softening temperature measurement method: Vicat softening temperature (at temperature rise rate of 50 /hour and load of 2.5N) was determined with a needle inserted by 1mm.
2 Shrinkage : A film gate sheet (126mm x 126mm x 2mm) was formed (at mold temperature of 40 and cooling period of 40 seconds) .
3 This is a grade that is made to order and sold.