



组件 - 塑料
UL 档案号: E173981

UBE CHEMICALS (ASIA) PUBLIC CO LTD

18th Floor, Sathorn Square Office Tower
No. 98 North Sathorn Rd
Silom, Bangrak,
Bangkok, 10500 Thailand

1013B

Polyamide 6 (PA6), pellets



可燃性	值	测试方法
UL 阻燃等级		UL 94
0.75 mm, ALL	V-2	IEC 60695-11-10, -20
1.5 mm, ALL	V-2	
3.0 mm, ALL	V-2	
6.0 mm, ALL	V-2	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746
1.5 mm	PLC 4	
3.0 mm	PLC 3	
6.0 mm	PLC 3	
高电弧燃烧指数(HAI)		UL 746
1.5 mm	PLC 0	
3.0 mm	PLC 0	
6.0 mm	PLC 0	
相比耐漏电起痕指数(CTI)	PLC 0	UL 746
介电强度	28 kV/mm	ASTM D149
高电压电弧起痕速率 (HVTR)	PLC 0	UL 746
体积电阻率	1.0E+14 ohms-cm	ASTM D257 IEC 60093
耐电弧性	PLC 6	ASTM D495
热性能	值	测试方法
RTI Elec		UL 746
0.75 mm	65.0 °C	
1.5 mm	65.0 °C	
3.0 mm	65.0 °C	
6.0 mm	65.0 °C	
RTI Imp		UL 746
0.75 mm	65.0 °C	
1.5 mm	65.0 °C	
3.0 mm	65.0 °C	
6.0 mm	65.0 °C	
RTI		UL 746
0.75 mm	65.0 °C	
1.5 mm	65.0 °C	
3.0 mm	65.0 °C	
6.0 mm	65.0 °C	
物理性能	值	测试方法
Dimensional Stability	0.0 %	ASTM D1042 ISO 2796