

TRIEX 3025U GRADE

DESCRIPTION

- TRIEX is the registered trademark of polycarbonate resin manufactured by Samyang Corporation. TRIEX polycarbonate resins offer superior mechanical properties, good dimensional stability and high electrical performance, which allows it to be widely used for electrical, electronic, appliance, automotive and optical industries.
- TRIEX 3025U is a UV stabilized polycarbonate resin grade which has a low melt viscosity and transparency in combination with superior physical properties.

CHARACTERISTICS

- High ultraviolet(UV) stability
- High flowability
- Good impact resistance
- Workable under a wide range of temperatures (-100°C ~ 135°C)
- High electrical performance
- Good dimensional stability
- Excellent transparency
- Low moisture absorbency
- Good weather resistance

APPLICATIONS

- TRIEX 3025U resin grade is used in out-door applications such as electric meter cover, window panes, sign board, wind break, signal lamps, and ship lights etc.

TYPICAL DATA OF TRIEX 3025U GRADE

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	—	D792	1.20
Water Absorption (24 hours at 23°C)	%	D570	0.15
Melt Flow Rate (270°C, 1.2kg)	g/10min	D1238	17
MECHANICAL			
Tensile Strength at yield	kg _f /cm ²	D638	670
Tensile Elongation at break	%	D638	120
Flexural Strength at yield	kg _f /cm ²	D790	880
Flexural Modulus	kg _f /cm ²	D790	23,000
Izod Impact Strength, notched, 23°C (1/8")	kg _f ·cm/cm	D256	77
Rockwell Hardness	R scale	D785	120
THERMAL			
HDT, 4.6 kg _f /cm ²	°C	D648	146
HDT, 18.6 kg _f /cm ²	°C	D648	132
Coefficient of Linear Thermal Expansion	mm/mm/°C	D696	5.6X10 ⁻⁵
ELECTRICAL			
Volume Resistivity	Ω·cm	D257	4X10 ¹⁶
Dielectric Strength	kV/mm	D149	30
Dielectric Constant, 60Hz	—	D150	2.85
Dissipation Factor, 60Hz	—	D150	0.0092
ARC Resistance	sec	D495	120
OTHERS			
UL-94 Flammability (1/16" thickness)	—	(UL 94)	V-2
Mold Shrinkage (3mm thickness)	%	D955	0.5~0.7

The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE FOR TRIEX 3025U GRADE

General processing conditions for TRIEX 3025U are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	°C	120
Drying Time	hr	3~5
Moisture Content, Max	%	0.02
Melt Temperature	°C	290 ~ 320
Nozzle Temperature	°C	290 ~ 310
Front Temperature	°C	290 ~ 310
Middle Temperature	°C	280 ~ 300
Rear Temperature	°C	270 ~ 290
Mold Temperature	°C	80 ~ 100
Back Pressure	MPa	0.3 ~ 0.7
Screw Speed	rpm	40 ~ 70
Vent Depth	mm	0.02 ~ 0.08

HEAD OFFICE

Samyang Corporation
263 yeonji-dong, Jongno-gu, Seoul, Korea. / TEL 82-2-740-7752 / FAX 82-2-740-7700

R&D CENTER

63-2 Hwaam-dong, yuseong-gu, Daejeon, Korea / TEL 82-42-865-8053 / FAX 82-42-865-8099

JEONJU PLANT

407 Palbok-dong 3-ga, Deokjin-gu, Jeonju, Krea / TEL 82-63-210-6660 / FAX 82-63-210-6677

SAMYANG KASEI

409 Palbok-dong 3-ga, Deokjin-gu, Jeonju, Krea / TEL 82-63-210-1114 / FAX 82-63-211-1240

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO.,LTD.

131, Shuangying-lu, Qingpu Gongyeyuan-qu,
Qingpu-qu, Shanghai, P.R.China / TEL 86-21-6922-2086 / FAX 86-21-6922-2271