



- [Products](#)[Business](#)[Application](#)[Product Line](#)[Corporate Profile](#)[Global Network](#)
- [Chemicals](#)[Construction Materials](#)[Machinery](#)

# POLYETHYLENE J1019

Print

UBE POLYETHYLENE (HP-LDPE)

- [Properties](#)[Additives](#)[Features](#)[Applications](#)

## Properties

Item	Unit	Nominal value	Test method
MFR	g/10min	10	ASTM D1238
Density	kg/m <sup>3</sup>	917	ASTM D1505
Melting point	°C	108	UBE method
Tensile strength	MPa	12	ASTM D638
Tensile elongation	%	450	ASTM D638
Flexural strength(Olsen)	MPa	130	ASTM D747
Hardness	(HDD)	47	ASTM D2240
Vicat softening point	°C	87	ASTM D1525
Brittle temperature	°C	-60	ASTM D746

- \* These values are typical properties and not to be considered as specifications.
- \* Specimens are prepared from compression-molded sheets.

## Additives

- Additive-free

## Features

- Moldability

## Applications

- Injection molding, Foamed molding
- Cap, Daily necessities