

# POLYETHYLENE UBEC530S

[Print](#)

UBE POLYETHYLENE (Wire &amp; Cable grade)

## Properties

## Features

## Applications

### Properties

Item	Unit	Nominal value	Test method
MFR	g/10min	1.2	ASTM D1238
Density	kg/m <sup>3</sup>	920	ASTM D1505
Tensile strength	MPa	18	ASTM D638
Tensile elongation	%	650	ASTM D638
Flexural strength(Olsen)	MPa	150	ASTM D747
Hardness	(HDD)	52	ASTM D2240
Vicat softening point	°C	91	ASTM D1525
Brittle temperature	°C	<-75	ASTM D746
Volume resistivity	Ω·m	10 <sup>14</sup> <	ASTM D257
Dielectric constant	(1 MHz)	2.3	ASTM D1531
Dissipation factor	(1 MHz×10 <sup>-3</sup> )	0.1	ASTM D1531
Dielectric strength	MV/m	36	ASTM D149

\* These values are typical properties and not to be considered as specifications.

\* Specimens are prepared from compression-molded sheets.

### Features

- Super-clean

### Applications

- CV-base. non-additive.