



- [Products](#)
- [Business](#)
- [Application](#)
- [Product Line](#)
- [Corporate Profile](#)
- [Global Network](#)
- [Chemicals](#)
- [Construction Materials](#)
- [Machinery](#)

# POLYETHYLENE Z322

[Print](#)

UBE POLYETHYLENE (HP-LDPE)

- [Properties](#)
- [Additives](#)
- [Features](#)
- [Applications](#)

## Properties

| Item                     | Unit              | Nominal value | Test method |
|--------------------------|-------------------|---------------|-------------|
| MFR                      | g/10min           | 1             | ASTM D1238  |
| Density                  | kg/m <sup>3</sup> | 933           | ASTM D1505  |
| Melting point            | °C                | 119           | UBE method  |
| Tensile strength         | MPa               | 14            | ASTM D638   |
| Tensile elongation       | %                 | 600           | ASTM D638   |
| Flexural strength(Olsen) | MPa               | 300           | ASTM D747   |
| Hardness                 | (HDD)             | 60            | ASTM D2240  |
| Vicat softening point    | °C                | 110           | ASTM D1525  |
| Brittle temperature      | °C                | <-75          | ASTM D746   |

- \* These values are typical properties and not to be considered as specifications.
- \* Specimens are prepared from compression-molded sheets.

## Additives

- Additive-free

## Features

- High rigidity, High transparency, High glossiness

## Applications

- Blown film
- Heat resistant LDPE film