

TRIEX SO4-3025UPNV

Polycarbonate Resin

Product Information

TYPICAL DATA OF TRIEX SO4-3025UPNV GRADE

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	D792	1.20
Water Absorption (24 hours at 23°C)	%	D570	0.15
Melt Flow Rate (300°C, 1.2kg)	g/10min	D1238	11
MECHANICAL			
Tensile Strength at yield	kg _f /cm ²	D638	600
Tensile Elongation at break	%	D638	100
Flexural Strength at yield	kg _f /cm ²	D638	880
Flexural Modulus	kg _f /cm ²	D1004	23,500
Izod Impact Strength, notched, 23°C (1/8")	kg _f ·cm/cm	D256	80
-40°C (1/8")	kg _f ·cm/cm	D256	43
THERMAL			
HDT, 18.6 kgf/cm ²	°C	D648	122
OTHERS			
UL-94 Flammability	-	(UL 94)	V-0@1.5mm &5VB@2.5mm(f1)
Mold Shrinkage	%	D955	0.4~0.8

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE FOR TRIEX SO4-3025UPNV GRADE

- General processing conditions for TRIEX SO4-3025UPNV are shown below.
Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	°C	120
Drying Time	hr	3~4
Moisture Content, Max	%	0.02
Melt Temperature	°C	280~300
Nozzle Temperature	°C	270~290
Front Temperature	°C	280~310
Middle Temperature	°C	270~310
Rear Temperature	°C	260~280
Mold Temperature	°C	65~105
Back Pressure	MPa	0.4~0.7
Screw Speed	%	40~70(slow to moderate)
Vent Depth	mm	0.02~0.08

Samyang Corporation

31 Jongno 33-gil, Jongno-gu, Seoul, Korea
TEL 82-2-740-7677 FAX 82-2-740-7700

R&D CENTER

730 Daedeokdae-ro, Yuseong-gu, Daejeon, Korea
TEL 82-42-865-8057 FAX 82-42-865-8099

JEONJU PLANT

147 Palbok-ro, Deokjin-gu, Jeonju, Jeollabuk-do, 54886, Korea
TEL 82-63-210-6670 FAX 82-63-210-6677

SAMYANG KASEI

376, Ongoeul-ro, Deokjin-gu, Jeonju-si,
Jeollabuk-do, 54886, Korea
TEL 82-63-210-1700 FAX 82-63-211-0301

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

131 Shuangying-Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
TEL 86-21-6922-2270 FAX 86-21-6922-2271

SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.

H-5100 Jászberény, Necső telep 1., Hungary
TEL 36-21-311-1256 FAX 36-21-311-1252