

TECHNICAL DATASHEET

TRAMID[®] 210G15

PA6

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	D792	1.24
Water Absorption (24 hours at 23°C)	%	D570	1.1
Melt Flow Rate (275°C, 2.16kg)	g/10min	D1238	24
MECHANICAL			
Tensile Strength at yield	kg _f /cm ²	D638	1,000
Tensile Elongation at break	%	D638	3
Flexural Strength at yield	kg _f /cm ²	D790	1,400
Flexural Modulus	kg _f /cm ²	D790	50,000
Izod Impact Strength, notched, 23°C (1/8")	kg _f ·cm/cm	D256	7
THERMAL			
HDT, 18.6 kg _f /cm ²	°C	D648	240
ELECTRICAL			
OTHERS			

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE

TRAMID[®] 210G15 GRADE

PA6

- General processing conditions for TRAMID210G15 are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	℃	70~80
Drying Time	hr	5~7
Moisture Content, Max	%	0.25
Melt Temperature	℃	270~290
Nozzle Temperature	℃	270~300
Front Temperature	℃	270~300
Middle Temperature	℃	260~290
Rear Temperature	℃	220~260
Mold Temperature	℃	20~70
Back Pressure	MPa	0.0~0.1
Screw Speed	rpm	10~50
Vent Depth	mm	0.02~0.08

Global Network

HEAD OFFICE

Samyang Corporation
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea
T. +82-2-740-7747

Chemical Research Center

730, Daedeok-daero, Yuseong-gu, Daejeon, Korea
T. +82-42-865-8114

JEONJU ENGINEERING PLASTIC PLANT

147, Palbok-ro, Deokjin-gu, Jeonju, Korea
T. +82-63-210-6664

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

No.131, Shuangying Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
T. +86-21-6922-2270

SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.

H5100, Jaszbereny, Necso, Telep 1, Hungary
T. +36-21-311-1263

SAMYANG ENGINEERING PLASTICS (VIETNAM) LLC

1 Song Hanh Road, Nhon Trach 6 Industrial Zone, Long Tho
Commune, Nhon Trach District, Dong Nai Province, Vietnam
T. +84-0251-3686-707