

TECHNICAL DATASHEET

TRICAP[®] UC45R

UD Tape

PROPERTY	UNIT	TYPICAL DATA
Material	-	PA6 CF
Fiber Contents	Vol %	50
Specific Gravity	-	1.45
Tensile Strength	MPa	1910
Tensile Modulus	GPa	95
Flexural Strength	MPa	1040
Flexural Modulus	GPa	85
Note	-	

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

Global Network

HEAD OFFICE

Samyang Corporation
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea
T. +82-2-740-7747

Chemical Research Center

730, Daedeok-daero, Yuseong-gu, Daejeon, Korea
T. +82-42-865-8114

DAEJEON ENGINEERING PLASTIC PLANT

9 Yuseong-daero, 1366-gil, Yuseong-gu, Daejeon, Korea
T. +82-42-867-3800

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

No.131, Shuangying Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
T. +86-21-6922-2270

SAMYANG ENGINEERING PLASTICS (GERMANY) CO., LTD.

8 Taunusanlage Frankfurt am Main,
HE 60329, Germany 855
T. +49 (0)162-579-6639