

TECHNICAL DATASHEET

TRIEL[®] 5402SP

TPEE

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	D792	1.13
Water Absorption (24 hours at 23°C)	%	D570	0.5
Melt Flow Rate (230°C, 2.16kg)	g/10min	D1238	5
MECHANICAL			
Tensile Strength at yield	kg _f /cm ²	D638	170
Tensile Elongation at break	%	D638	>400
Flexural Strength at yield	kg _f /cm ²	D790	37
Flexural Modulus	kg _f /cm ²	D790	620
Izod Impact Strength, notched, 23°C (1/8")	kg _f ·cm/cm	D256	No Break
Hardness (Shore D)	Shore D		40
THERMAL			
HDT, 18.6 kgf/cm ²	°C	D648	57
Vicat softening temperature	°C		142
ELECTRICAL			
OTHERS			
Mold Shrinkage (3mm thickness)	%	D955	1.5 ~ 1.7

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE

TRIEL[®] 5402SP GRADE

TPEE

- General processing conditions for TRIEL5402SP are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	℃	90~100
Drying Time	hr	3~4
Moisture Content, Max	%	0.02
Melt Temperature	℃	180~210
Nozzle Temperature	℃	180~210
Front Temperature	℃	180~210
Middle Temperature	℃	180~210
Rear Temperature	℃	170~190
Mold Temperature	℃	30~50
Back Pressure	MPa	0.0~0.1
Screw Speed	rpm	10~50
Vent Depth	mm	0.02~0.08

Global Network

HEAD OFFICE

Samyang Corporation
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea
T. +82-2-740-7747

Chemical Research Center

730, Daedeok-daero, Yuseong-gu, Daejeon, Korea
T. +82-42-865-8114

JEONJU ENGINEERING PLASTIC PLANT

147, Palbok-ro, Deokjin-gu, Jeonju, Korea
T. +82-63-210-6664

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

No.131, Shuangying Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
T. +86-21-6922-2270

SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.

H5100, Jaszbereny, Necso, Telep 1, Hungary
T. +36-21-311-1263

SAMYANG ENGINEERING PLASTICS (VIETNAM) LLC

1 Song Hanh Road, Nhon Trach 6 Industrial Zone, Long Tho
Commune, Nhon Trach District, Dong Nai Province, Vietnam
T. +84-0251-3686-707