



Component - Plastics

File Number: E121254

SAMYANG CORPORATION

407 3-Ga Palbok-Dong

Cheonju, YKCheonbuk 560-200 Korea, Republic of



TRILOY: 120(+)

Polybutylene Terephthalate/Polycarbonate (PBT/PC), pellets

(+) - Represent any one letter, except 200N, 210N and 210NHF

Flammability	Value	Test Method
Flame Rating		
1.5 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
Thermal	Value	Test Method
RTI Elec		UL 746
1.5 mm	75.0 °C	
3.0 mm	75.0 °C	
RTI Imp		UL 746
1.5 mm	75.0 °C	
3.0 mm	75.0 °C	
RTI Str		UL 746
1.5 mm	75.0 °C	
3.0 mm	75.0 °C	