



Component - Plastics

File Number: E121254

SAMYANG CORPORATION

407 3-Ga Palbok-Dong

Cheonju, YKCheonbuk 560-200 Korea, Republic of



TRILOY: 170N2

Polycarbonate/Polybutylene Terephthalate (PC/PBT), pellets

Flammability	Value	Test Method
Flame Rating		UL 94
1.5 mm, ALL	V-2	IEC 60695-11-10, -20
3.0 mm, ALL	V-2	
Thermal	Value	Test Method
RTI Elec		UL 746
1.5 mm	75.0 °C	
3.0 mm	75.0 °C	
RTI Imp		UL 746
1.5 mm	75.0 °C	
3.0 mm	75.0 °C	
RTI Str		UL 746
1.5 mm	75.0 °C	
3.0 mm	75.0 °C	