



Component - Plastics

File Number: E121254

SAMYANG CORPORATION

407 3-Ga Palbok-Dong

Cheonju, YKCheonbuk 560-200 Korea, Republic of



TRILOY: 410

Polybutylene Terephthalate/Polycarbonate (PBT/PC), pellets

Flammability	Value	Test Method
Flame Rating		
1.5 mm, ALL	HB	UL 94
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
Thermal	Value	Test Method
RTI Elec (1.5 mm)	75.0 °C	UL 746
RTI Imp (1.5 mm)	75.0 °C	UL 746
RTI Str (1.5 mm)	75.0 °C	UL 746