

## TECHNICAL DATASHEET

**TRILOY® 200FT**

PC/ABS

| PROPERTY                                   | UNIT                             | ASTM METHOD | TYPICAL DATA |
|--------------------------------------------|----------------------------------|-------------|--------------|
| <b>PHYSICAL</b>                            |                                  |             |              |
| Specific Gravity                           | -                                | D792        | 1.08         |
| Water Absorption (24 hours at 23°C)        | %                                | D570        | 0.2          |
| Melt Flow Rate (250°C, 5kg)                | g/10min                          | D1238       | 26           |
| <b>MECHANICAL</b>                          |                                  |             |              |
| Tensile Strength at yield                  | kg <sub>f</sub> /cm <sup>2</sup> | D638        | 550          |
| Tensile Elongation at break                | %                                | D638        | 50           |
| Flexural Strength at yield                 | kg <sub>f</sub> /cm <sup>2</sup> | D790        | 850          |
| Flexural Modulus                           | kg <sub>f</sub> /cm <sup>2</sup> | D790        | 23,000       |
| Izod Impact Strength, notched, 23°C (1/8") | kg <sub>f</sub> ·cm/cm           | D256        | 65           |
| Rockwell Hardness                          | R scale                          | D785        | 100          |
| <b>THERMAL</b>                             |                                  |             |              |
| HDT, 18.6 kgf/cm <sup>2</sup>              | °C                               | D648        | 100          |
| <b>ELECTRICAL</b>                          |                                  |             |              |
| <b>OTHERS</b>                              |                                  |             |              |
| Mold Shrinkage (3mm thickness)             | %                                | D955        | 0.5~0.7      |

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

## PROCESSING GUIDE

# TRILOY® 200FT GRADE

PC/ABS

- General processing conditions for TRILOY200FT are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

| SPECIFICATION         | UNIT | CONDITIONS |
|-----------------------|------|------------|
| Drying Temperature    | ℃    | 80-90      |
| Drying Time           | hr   | 3-5        |
| Moisture Content, Max | %    | 0.02       |
| Melt Temperature      | ℃    | 240~270    |
| Nozzle Temperature    | ℃    | 245-255    |
| Front Temperature     | ℃    | 250-260    |
| Middle Temperature    | ℃    | 250-260    |
| Rear Temperature      | ℃    | 240-250    |
| Mold Temperature      | ℃    | 60-90      |

## Global Network

### HEAD OFFICE

Samyang Corporation  
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea  
T. +82-2-740-7747

### Chemical Research Center

730, Daedeok-daero, Yuseong-gu, Daejeon, Korea  
T. +82-42-865-8114

### JEONJU ENGINEERING PLASTIC PLANT

147, Palbok-ro, Deokjin-gu, Jeonju, Korea  
T. +82-63-210-6664

### SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

No.131, Shuangying Road, Qingpu Industrial Area,  
Qingpu County, Shanghai, China  
T. +86-21-6922-2270

### SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.

H5100, Jaszbereny, Necso, Telep 1, Hungary  
T. +36-21-311-1263

### SAMYANG ENGINEERING PLASTICS (VIETNAM) LLC

1 Song Hanh Road, Nhon Trach 6 Industrial Zone, Long Tho  
Commune, Nhon Trach District, Dong Nai Province, Vietnam  
T. +84-0251-3686-707