

TECHNICAL DATASHEET

TRILOY® 200NH

PC/ABS

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	D792	1.17
Water Absorption (24 hours at 23°C)	%	D570	0.2
Melt Flow Rate (260°C, 2.16kg)	g/10min	D1238	13
MECHANICAL			
Tensile Strength at yield	kg _f /cm ²	D638	550
Tensile Elongation at break	%	D638	60
Flexural Strength at yield	kg _f /cm ²	D790	850
Flexural Modulus	kg _f /cm ²	D790	26,000
Izod Impact Strength, notched, 23°C (1/8")	kg _f ·cm/cm	D256	50
Rockwell Hardness	R scale	D785	115
THERMAL			
HDT, 18.6 kgf/cm ²	°C	D648	85
Coefficient of Linear Thermal Expansion	mm/mm/°C	D696	8.3 x 10 ⁻⁵
ELECTRICAL			
Volume Resistivity	Ω·cm	D257	9E+16
Dielectric Strength	kV/mm	D149	30
Dielectric Constant	-	D150	3
Dissipation Factor	-	D150	0.009
ARC Resistance	sec	D495	120
OTHERS			
UL-94 Flammability (1.7mm thickness)	-	(UL 94)	V-0, 5VB
Mold Shrinkage (3mm thickness)	%	D955	0.5~0.7

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE

TRILOY® 200NH GRADE

PC/ABS

- General processing conditions for TRILOY200NH are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	℃	90
Drying Time	hr	3-5
Moisture Content, Max	%	0.02
Melt Temperature	℃	260~280
Nozzle Temperature	℃	250~270
Front Temperature	℃	255~275
Middle Temperature	℃	255~275
Rear Temperature	℃	245~265
Mold Temperature	℃	60~90

Global Network

HEAD OFFICE

Samyang Corporation
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea
T. +82-2-740-7747

Chemical Research Center

730, Daedeok-daero, Yuseong-gu, Daejeon, Korea
T. +82-42-865-8114

JEONJU ENGINEERING PLASTIC PLANT

147, Palbok-ro, Deokjin-gu, Jeonju, Korea
T. +82-63-210-6664

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

No.131, Shuangying Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
T. +86-21-6922-2270

SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.

H5100, Jaszbereny, Necso, Telep 1, Hungary
T. +36-21-311-1263

SAMYANG ENGINEERING PLASTICS (VIETNAM) LLC

1 Song Hanh Road, Nhon Trach 6 Industrial Zone, Long Tho
Commune, Nhon Trach District, Dong Nai Province, Vietnam
T. +84-0251-3686-707