

TECHNICAL DATASHEET

TRILOY® TP260W

PC/ABS

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	D792	1.30
Water Absorption (24 hours at 23°C)	%	D570	0.2
Melt Flow Rate (260°C, 2.16kg)	g/10min	D1238	18
MECHANICAL			
Tensile Strength at yield	kg _f /cm ²	D638	500
Tensile Elongation at break	%	D638	10
Flexural Strength at yield	kg _f /cm ²	D790	750
Flexural Modulus	kg _f /cm ²	D790	45,000
Izod Impact Strength, notched, 23°C (1/8")	kg _f ·cm/cm	D256	3
THERMAL			
HDT, 18.6 kg _f /cm ²	°C	D648	86
ELECTRICAL			
OTHERS			
UL-94 Flammability (1.4mm thickness)	-	(UL 94)	V-0
Mold Shrinkage (3mm thickness)	%	D955	0.2~0.4

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE

TRILOY® TP260W GRADE

PC/ABS

- General processing conditions for TRILOYTP260W are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	℃	80
Drying Time	hr	3~4
Moisture Content, Max	%	0.02
Melt Temperature	℃	250~270
Nozzle Temperature	℃	250~270
Front Temperature	℃	250~270
Middle Temperature	℃	240~265
Rear Temperature	℃	230~250
Mold Temperature	℃	40~80
Back Pressure	MPa	0.4~0.6
Screw Speed	rpm	50~60
Vent Depth	mm	0.02~0.08
Injection Pressure	MPa	50~80
Injection Speed	%	20~50
Hold Pressure	MPa	35~60
Injection Cushion	mm	3~6

Global Network

HEAD OFFICE

Samyang Corporation
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea
T. +82-2-740-7747

JEONJU ENGINEERING PLASTIC PLANT

147, Palbok-ro, Deokjin-gu, Jeonju, Korea
T. +82-63-210-6664

SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.

H5100, Jaszbereny, Necso, Telep 1, Hungary
T. +36-21-311-1263

Chemical Research Center

730, Daedeok-daero, Yuseong-gu, Daejeon, Korea
T. +82-42-865-8114

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

No.131, Shuangying Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
T. +86-21-6922-2270

SAMYANG ENGINEERING PLASTICS (VIETNAM) LLC

1 Song Hanh Road, Nhon Trach 6 Industrial Zone, Long Tho
Commune, Nhon Trach District, Dong Nai Province, Vietnam
T. +84-0251-3686-707