

TECHNICAL DATASHEET

TRIMMA® FT6125

Modified PMMA

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	D792	1.18
Melt Flow Rate (220℃, 10kg)	g/10min	D1238	25
MECHANICAL			
Tensile Strength at yield	kg _f /cm ²	D638	630
Tensile Elongation at break	%	D638	20
Flexural Strength at yield	kg _f /cm ²	D790	850
Flexural Modulus	kg _f /cm ²	D790	24,000
Izod Impact Strength, notched, 23℃ (1/8")	kg _f ·cm/cm	D256	1.8
Rockwell Hardness	R scale	D785	118
THERMAL			
HDT, 18.6 kg _f /cm ²	℃	D648	75
ELECTRICAL			
OTHERS			
UL-94 Flammability	-	(UL 94)	HB
Mold Shrinkage (3mm thickness)	%	D955	0.5 ~ 0.7

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE

TRIMMA® FT6125 GRADE

Modified PMMA

- General processing conditions for TRIMMAFT6125 are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	℃	75
Drying Time	hr	3-5
Moisture Content, Max	%	0.02
Melt Temperature	℃	220-240
Nozzle Temperature	℃	220-240
Front Temperature	℃	210-230
Middle Temperature	℃	210-230
Rear Temperature	℃	190-200
Mold Temperature	℃	50-80
Back Pressure	MPa	0.3-0.5
Screw Speed	rpm	40-70
Vent Depth	mm	0.02-0.08

Global Network

HEAD OFFICE

Samyang Corporation
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea
T. +82-2-740-7747

Chemical Research Center

730, Daedeok-daero, Yuseong-gu, Daejeon, Korea
T. +82-42-865-8114

JEONJU ENGINEERING PLASTIC PLANT

147, Palbok-ro, Deokjin-gu, Jeonju, Korea
T. +82-63-210-6664

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

No.131, Shuangying Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
T. +86-21-6922-2270

SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.

H5100, Jaszbereny, Necso, Telep 1, Hungary
T. +36-21-311-1263

SAMYANG ENGINEERING PLASTICS (VIETNAM) LLC

1 Song Hanh Road, Nhon Trach 6 Industrial Zone, Long Tho
Commune, Nhon Trach District, Dong Nai Province, Vietnam
T. +84-0251-3686-707