

TECHNICAL DATASHEET

TRIMMA® SD6350H

Modified PMMA

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	D792	1.09
Water Absorption (24 hours at 23°C)	%	D570	0.02
Melt Flow Rate (220°C, 10kg)	g/10min	D1238	16
MECHANICAL			
Tensile Strength at yield	kg _f /cm ²	D638	550
Tensile Elongation at break	%	D638	20
Flexural Strength at yield	kg _f /cm ²	D790	720
Flexural Modulus	kg _f /cm ²	D790	26,000
Izod Impact Strength, notched, 23°C (1/8")	kg _f ·cm/cm	D256	7
THERMAL			
HDT, 18.6 kg _f /cm ²	°C	D648	88
ELECTRICAL			
OTHERS			
Mold Shrinkage (3mm thickness)	%	D955	0.5 ~ 0.7

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE

TRIMMA® SD6350H GRADE

Modified PMMA

- General processing conditions for TRIMMASD6350H are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	℃	70-80
Drying Time	hr	3-4
Moisture Content, Max	%	0.02
Melt Temperature	℃	220-240
Nozzle Temperature	℃	220-240
Front Temperature	℃	210-230
Middle Temperature	℃	210-230
Rear Temperature	℃	190-200
Mold Temperature	℃	50-80
Back Pressure	MPa	0.3-0.5
Screw Speed	rpm	40-70
Vent Depth	mm	0.02-0.08

Global Network

HEAD OFFICE

Samyang Corporation
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea
T. +82-2-740-7747

Chemical Research Center

730, Daedeok-daero, Yuseong-gu, Daejeon, Korea
T. +82-42-865-8114

JEONJU ENGINEERING PLASTIC PLANT

147, Palbok-ro, Deokjin-gu, Jeonju, Korea
T. +82-63-210-6664

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

No.131, Shuangying Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
T. +86-21-6922-2270

SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.

H5100, Jaszbereny, Necso, Telep 1, Hungary
T. +36-21-311-1263

SAMYANG ENGINEERING PLASTICS (VIETNAM) LLC

1 Song Hanh Road, Nhon Trach 6 Industrial Zone, Long Tho
Commune, Nhon Trach District, Dong Nai Province, Vietnam
T. +84-0251-3686-707