



Component - Plastics

File Number: E121254

SAMYANG CORPORATION

407 3-Ga Palbok-Dong
Cheonju, YKCheonbuk 560-200 Korea, Republic of



TRIEX: 3500G-(z)

Polycarbonate (PC), pellets

(z) - Represents any number 20-29 incl.

Flammability	Value	Test Method
Flame Rating		UL 94
1.5 mm, ALL	V-0	IEC 60695-11-10, -20
3.0 mm, ALL	V-0	
6.0 mm, ALL	V-0	
Electrical	Value	Test Method
Hot-wire Ignition (HWI)		UL 746
1.5 mm	PLC 2	
3.0 mm	PLC 1	
6.0 mm	PLC 0	
High Amp Arc Ignition (HAI)		UL 746
1.5 mm	PLC 0	
3.0 mm	PLC 0	
6.0 mm	PLC 0	
Comparative Tracking Index (CTI)	PLC 3	UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 3	UL 746
Arc Resistance	PLC 7	ASTM D495
Thermal	Value	Test Method
RTI Elec		UL 746
1.5 mm	130 °C	
3.0 mm	130 °C	
6.0 mm	130 °C	
RTI Imp		UL 746
1.5 mm	125 °C	
3.0 mm	125 °C	
6.0 mm	125 °C	
RTI Str		UL 746
1.5 mm	130 °C	
3.0 mm	130 °C	
6.0 mm	130 °C	