## TRIREX® EM3022U

PC

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	D792	1.20
Water Absorption (24 hours at 23℃)	%	D570	0.12
Melt Flow Rate (300°c, 1.2kg)	g/10min	D1238	10
MECHANICAL			
Tensile Strength at yield	kg <sub>f</sub> /cm²	D638	600
Tensile Elongation at break	%	D638	120
Flexural Strength at yield	kg <sub>f</sub> /cm²	D790	800
Flexural Modulus	kg <sub>f</sub> /cm²	D790	20,000
Izod Impact Strength, notched, 23°C (1/8")	kg <sub>f</sub> ·cm/cm	D256	70
THERMAL			
HDT, 18.6 kgf/cm²	°C	D648	130
ELECTRICAL			
OTHERS			
UL-94 Flammability (0.8mm thickness)	-	(UL 94)	V-2

<sup>\*</sup> The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

