

TECHNICAL DATASHEET

TRIEX[®] NH3025NP

PC

PROPERTY	UNIT	ASTM METHOD	TYPICAL DATA
PHYSICAL			
Specific Gravity	-	D792	1.20
Water Absorption (24 hours at 23°C)	%	D570	0.13
Melt Flow Rate (300°C, 1.2kg)	g/10min	D1238	20
MECHANICAL			
Tensile Strength at yield	kg _f /cm ²	D638	620
Tensile Elongation at break	%	D638	120
Flexural Strength at yield	kg _f /cm ²	D790	850
Flexural Modulus	kg _f /cm ²	D790	21,000
Izod Impact Strength, notched, 23°C (1/8")	kg _f ·cm/cm	D256	70
Rockwell Hardness	R scale	D785	120
THERMAL			
HDT, 18.6 kgf/cm ²	°C	D648	116
Coefficient of Linear Thermal Expansion	mm/mm/°C	D696	5.6 x 10 ⁻⁵
ELECTRICAL			
Volume Resistivity	Ω·cm	D257	4E+16
Dielectric Strength	kV/mm	D149	30
Dielectric Constant	-	D150	2.85
Dissipation Factor	-	D150	0.0092
ARC Resistance	sec	D495	90
OTHERS			
UL-94 Flammability (1.5mm thickness)	-	(UL 94)	V-0, 5VB
Mold Shrinkage (3mm thickness)	%	D955	0.5-0.7

※ The figures listed in this table are typical values obtained under the standard test methods and may not be applicable for products that are under different application condition.

PROCESSING GUIDE

TRIREX[®] NH3025NP GRADE

PC

- General processing conditions for TRIREXNH3025NP are shown below. Drying prior to processing is essential to ensure desired appearance and property performance.

SPECIFICATION	UNIT	CONDITIONS
Drying Temperature	℃	110
Drying Time	hr	3-5
Moisture Content, Max	%	0.02
Melt Temperature	℃	270-300
Nozzle Temperature	℃	260-290
Front Temperature	℃	260-280
Middle Temperature	℃	255-275
Rear Temperature	℃	250-270
Mold Temperature	℃	50-80
Back Pressure	MPa	0.3-0.7
Screw Speed	rpm	40-70
Vent Depth	mm	0.025-0.076

Global Network

HEAD OFFICE

Samyang Corporation
31, Jong-ro 33-gil, Jongno-gu, Seoul, Korea
T. +82-2-740-7747

Chemical Research Center

730, Daedeok-daero, Yuseong-gu, Daejeon, Korea
T. +82-42-865-8114

JEONJU ENGINEERING PLASTIC PLANT

147, Palbok-ro, Deokjin-gu, Jeonju, Korea
T. +82-63-210-6664

SAMYANG ENGINEERING PLASTICS (SHANGHAI) CO., LTD.

No.131, Shuangying Road, Qingpu Industrial Area,
Qingpu County, Shanghai, China
T. +86-21-6922-2270

SAMYANG ENGINEERING PLASTICS (HUNGARY) CO., LTD.

H5100, Jaszbereny, Necso, Telep 1, Hungary
T. +36-21-311-1263

SAMYANG ENGINEERING PLASTICS (VIETNAM) LLC

1 Song Hanh Road, Nhon Trach 6 Industrial Zone, Long Tho
Commune, Nhon Trach District, Dong Nai Province, Vietnam
T. +84-0251-3686-707