

UBESTA 3030JI6L

[Print](#)

Engineering Plastics

Dry as molded

		Unit	Test method	Measured value
Melting temperature		° C	ISO 11357-3	176
Density		g/cm ³	ISO 1183-3	1.00
Tensile stress at yield		MPa	ISO 527-1,2	29
Tensile strain at yield		%	ISO 527-1,2	19
Tensile strain at break		%	ISO 527-1,2	> 150
Flexural strength		MPa	ISO 178	23
Flexural modulus		MPa	ISO 178	500
Shore hardness	D-scale	-	ISO 868	67
Rockwell hardness	R-scale	-	ISO 2039-2	59
Impact strength (Charpy, Notched)	23 ° C	kJ/m ²	ISO 179/1eA	115P
	-40 ° C	kJ/m ²	ISO 179/1eA	15C
Temp. of deflection under load	0.45 MPa	° C	ISO 75-2	80
	1.8 MPa	° C	ISO 75-2	42
Moulding shrinkage (In flow direction/ In transverse direction)		%	ISO 294-4	0.7/2.0
Abrasion loss (CS-17. 1,000 rev.)		mg	ISO 9352	7
Coef. Of linear thermal expansion		10 ⁻⁴ /K	ISO 11359-2	1.8
Volume resistivity		Ω·cm	IEC 60093	10 ¹⁴
Moisture absorption (24 h in water at 23 ° C)		%	ISO 62	0.7
Melt flow rate(250 ° C/5,000 g)		g/10 min	ISO 1133	3
Comments				Tubing Impact modified
Color				Black

Impact Strength:N=not broken P=partially broken C=completely broken