

Technical Data Sheet



ALCOM ABS 530/22 SV1287-04MCS

MOCOM

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Colour	metallic effect
Special Features	good flow
Application Area	domestic appliances
Typical Applications	housings

Pre-Drying Conditions	80 °C in an air circulating dryer for 3-6 h 80 °C in a dry air (dessiccant) dryer for 2-4 h dependant on moisture content
Processing Injection Moulding	melt temperature 220-260 °C mould temperature 50-80 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2600	MPa	ISO 178
Flexural Stress (3.5% Strain)	66	MPa	ISO 178
Tensile Modulus	2300	MPa	ISO 527
Tensile Stress at Yield	43	MPa	ISO 527
Tensile Elongation at Yield	2.3	%	ISO 527
Tensile Elongation at Break	12	%	ISO 527
Impact Strength (Charpy, 23°C)	48	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	43	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	13	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	5	kJ/m ²	ISO 179/1eA
Ball Indentation Hardness H358/30	100	MPa	ISO 2039-1
Thermal Properties			
Vicat B50	96	°C	ISO 306
HDT / A (1,8 MPa)	85	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	18	cm ³ /10min	ISO 1133
MVR temperature	220	°C	-
MVR load	10	kg	-
Shrinkage (lengthwise, 24h)	0.5 - 0.7	%	ISO 294-4
Shrinkage (lateral, 24h)	0.5 - 0.7	%	ISO 294-4
Physical Properties			
Density	1050	kg/m ³	ISO 1183