

Technical Data Sheet



ALTECH ABS A 1000/172 UV

MOCOM

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Filler/Additive System	light stabiliser
Colour	grey, white
Special Features	good flow, processing stabilised, UV stabilised, heat stabilised
Market Segment	Information Technology, electrical and electronic, various
Application Area	telecommunications, consumer electronics
Typical Applications	display elements, keyboards

Pre-Drying Conditions	80 °C in an air circulating dryer for 3-6 h 80 °C in a dry air (dessiccant) dryer for 2-4 h dependant on moisture content max. moisture content <0,20 %
Processing Injection Moulding	melt temperature 200-240 °C mould temperature 50-80 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2400	MPa	ISO 178
Flexural Stress (3.5% Strain)	70	MPa	ISO 178
Tensile Modulus	2500	MPa	ISO 527
Tensile Stress at Yield	45	MPa	ISO 527
Tensile Elongation at Yield	2.5	%	ISO 527
Tensile Elongation at Break	20	%	ISO 527
Impact Strength (Charpy, 23°C)	80	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	65	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	12	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	6	kJ/m ²	ISO 179/1eA
Ball Indentation Hardness H358/30	110	MPa	ISO 2039-1
Thermal Properties			
Vicat B50	95	°C	ISO 306
HDT / A (1,8 MPa)	80	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	30	cm ³ /10min	ISO 1133
MVR temperature	220	°C	-
MVR load	10	kg	-
Shrinkage (24h)	0.3 - 0.7	%	ISO 294-4
Physical Properties			
Density	1100	kg/m ³	ISO 1183