

Technical Data Sheet



ALTECH ABS A 1000/227 UV

MOCOM

Base Polymer	Acrylonitrile/Butadiene/Styrene/Copolymer
Filler/Additive System	light stabiliser
Colour	white
Special Features	UV stabilised, heat stabilised, processing stabilised
Market Segment	various, building and construction
Application Area	injection moulded parts
Typical Applications	housings, clothing / fasteners

Pre-Drying Conditions	80 °C in a dry air (dessiccant) dryer for 2-4 h 80 °C in an air circulating dryer for 3-6 h dependant on moisture content max. moisture content <0,20 %
Processing Injection Moulding	melt temperature 200-240 °C mould temperature 50-80 °C
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2500	MPa	ISO 178
Flexural Stress (3.5% Strain)	66	MPa	ISO 178
Tensile Modulus	2400	MPa	ISO 527
Tensile Stress at Yield	44	MPa	ISO 527
Tensile Elongation at Yield	2.2	%	ISO 527
Tensile Elongation at Break	15	%	ISO 527
Impact Strength (Charpy, 23°C)	100	kJ/m²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	75	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	16	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	6	kJ/m²	ISO 179/1eA
Ball Indentation Hardness H358/30	100	MPa	ISO 2039-1
Thermal Properties			
Vicat B50	92	°C	ISO 306
HDT / A (1,8 MPa)	80	°C	ISO 75-1/-2
Rheological Properties			
Melt Index (MVR)	35	cm³/10min	ISO 1133
MVR temperature	220	°C	-
MVR load	10	kg	-
Physical Properties			
Density	1060	kg/m³	ISO 1183