

Novodur® 240
ABS

INEOS Styrolution

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	20	cm³/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield stress	49	MPa	ISO 527

Thermal Properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	100	°C	ASTM D 1525

Characteristics

Processing

Injection Molding

Applications

Electrical and Electronical, Sports Equipment

Delivery form

Pellets