

Novodur® 532
ABS

INEOS Styrolution

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	2.5	cm³/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield stress	38	MPa	ISO 527

Thermal Properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	95	°C	ASTM D 1525

Characteristics

Processing

Sheet Extrusion, Other Extrusion

Special Characteristics

Impact modified

Delivery form

Pellets

Applications

Sports Equipment